

SLURRY AND METHOD FOR CHEMICAL MECHANICAL POLISHING OF METAL  
STRUCTURES INCLUDING REFRACTORY METAL BASED BARRIER LAYERS

Inventors: Rajiv. K Singh  
Seung-Mahn Lee

UNIVERSITY OF FLORIDA

(UF Disclosure No. 10690)

AKERMAN SENTERFITT

DOCKET No.: 5853-224

EXPRESS MAIL #EL920521858US

202220" 01023001

# SLURRY AND METHOD FOR CHEMICAL MECHANICAL POLISHING OF METAL STRUCTURES INCLUDING REFRACTORY METAL BASED BARRIER LAYERS

## STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

Not applicable

### Field of the Invention

This invention relates to a slurry and method for chemical-mechanical polishing of structures including refractory metal based barrier layers.

### Background

10082030-02202  
202220-02202

Reductions in semiconductor device dimensions provide higher densities and improved performance for integrated circuits. In many integrated electronic devices, millions of discrete elements, such as transistors, resistors and capacitors, are interconnected. Due to an increase in device density provided by scaling of semiconductor processes to improve circuit performance, it is no longer generally possible to utilize a single metal interconnect level. Single level interconnects result in significant parasitic resistance which can adversely affect device performance, particularly the dynamic performance of the integrated circuit.

Copper has become an increasingly popular choice for interconnect metal and has begun replacing aluminum in certain applications. Copper is much more conductive than aluminum, allowing finer wires having lower resistive losses. Copper is also significantly less vulnerable to electromigration than aluminum and less likely to fracture under stress. Electromigration is the

drift of metal atoms when a conductor carries high current densities, and can create reliability problems through generation of voids and other defects.

Although copper provides advantages over aluminum, it has at least one major disadvantage. Copper is poisonous to silicon since it readily diffuses into silicon and causes deep-level defects. Therefore, copper must be isolated from silicon, usually through the use of a suitable refractory metal based barrier layer.

Multilevel metallization structures have been developed which include an interconnection structure having several levels of metallization separated by thin insulating layers. Metal plugs are used to connect the different metal levels to one another. Presently, aluminum alloys (e.g. Al/Si/Cu) are still commonly used for the metal interconnect, while tungsten is generally used for plug structures as the material of choice for interconnecting two levels of metals. Aluminum and its alloys are generally dry etched, such as by reactive ion etching and plasma etching. However, dry etching of copper is not currently feasible. Accordingly, when copper and its alloys are used instead of conventional aluminum or aluminum alloys as an interconnection material, alternative techniques are employed to define the copper lines.

For example, a damascene process together with chemical-mechanical polishing (CPM) can be used to define copper lines. In a damascene process, trenches are etched in a dielectric material, such as silicon dioxide ( $\text{SiO}_2$ ). A barrier material is then deposited, generally by sputtering. Copper is then deposited typically using electrodeposition techniques (e.g. electroplating) to fill the barrier lined trenches. The overburden regions of the copper film are then removed by CMP to define the copper lines.

CMP combines both chemical action and mechanical forces and is commonly used to remove metal overlayers in damascene processes, remove excess oxide in shallow trench isolation steps and to reduce topography across a dielectric region. Components required for CMP include a chemically reactive liquid medium and a polishing surface to provide the mechanical control required to achieve planarity.

Either the liquid or the polishing surface may contain nano-size inorganic particles to enhance the reactive and mechanical activity of the process. Typically, a chemically modified thin layer on the wafer surface is formed, such as a metal oxide, and then abrasives are used to remove the chemically modified layer from the surface. Once the surface layer is removed, a thin passive film is reformed rapidly on the surface and controls the removal process. CMP is the only technique currently known for producing die level flatness required for sub 0.5  $\mu\text{m}$  devices and is considered a requirement for the production of sub 0.2  $\mu\text{m}$  device structures and state-of-the-art metal interconnect schemes.

Metals can also be used to form the gate electrode of certain devices. In this case, the metal gate can provide the electrical pathway for switching the device. In the case of a MOS transistor, the gate dielectric is typically silicon dioxide while the typical gate electrodes presently used are generally formed from heavily doped polysilicon. Alternative gate dielectrics having improved properties may soon replace  $\text{SiO}_2$ . For example, novel high dielectric constant materials such as yttria stabilized zirconia (YSZ), hafnia, lanthanum oxide, and certain silicates are expected to find increasing use for future high performance applications.

To use novel high dielectric constant gate dielectrics more efficiently, gate electrode materials such as Ta, Cu and Pt may also become used. Other possible metallic materials may

include Os, Ru, TiN, TaSiN, IrO<sub>2</sub>, RuO<sub>2</sub> and other conducting oxides such as tin oxide (SnO<sub>2</sub>), indium tin oxide, and related mixtures and alloys. Copper may be deposited on top of these material systems. Besides the use of copper in interconnects for CMOS devices and gate structures in high dielectric constant materials, there may be number of emerging applications such as ferroelectric random access memory devices (FeRAM), tunneling magnetoresistance (TMR) or giant magnetoresistance (GMR) devices where copper is deposited on a metal or a dielectric structure. In a FeRAM, copper may be used as the interconnecting metal or as sandwich metal layer on a gate electrode system. In a TMR or a GMR device, copper can be used as a back terminal, front end terminal or an electrode on a multilayer magnetic/non-magnetic structure. To create these specific structures it is also essential to remove copper selectively from the surface, but not to remove the underlying dielectric or metallic material.

The dielectric used in multiple level interconnect structures is typically silicon dioxide or doped silicon dioxide. With the rapid progression in device speeds to 1 GHz or more, circuit performance becomes increasingly limited by the interconnect system.

Thus, it has become increasingly important to use dielectric materials which have a dielectric constant (K) below that of silicon dioxide, silicon dioxide having a K of approximately 4.

Dielectrics which have a dielectric constant less than 4 are typically referred to as "low K" materials. Examples of low K materials which may find increasing use as device speeds increase include doped silicon oxide, such as BLACK DIAMOND®, produced by the Applied Materials Corporation, Santa Clara, CA.

Introducing low K dielectric materials as inter-metal dielectric can produces a major improvement to device performance by lowering the line-to-line capacitance which increases

device speed by reducing interconnect RC delay. These materials also can reduce cross-talk noise in the interconnect and can alleviate power dissipation issues.

Figure 1 shows a schematic view of the steps in a copper damascene CMP process. A low dielectric constant material disposed on a silicon wafer is patterned by suitable etching to form a plurality of trenches 110 as shown in FIG. 1(a). A diffusion barrier layer 120, such as Ti, Ta, WN, TaSiN or TaN, is then applied to cover the wafer surface, including the trenches 110 as shown in FIG. 1(b). A copper or copper alloy layer 130 is then deposited, by a method such as electroplating. (FIG. 1(c)). The copper or copper alloy layer is isolated from the remainder of the circuit by the barrier layer 120. Copper (or metal in general) disposed over dielectric plateaus is commonly referred to as overburden metal 131.

A CMP process can then be used to define the copper layer through an essentially planar removal process. The CMP process proceeds to remove the copper layer sufficient to remove the overburden portion 131 to expose the barrier layer in the overburden regions to produce the structure 140 shown in FIG. 1(d). A second CMP step, generally using a different slurry as compared to the copper CMP process, is then used to polish the barrier layer and produce the completed structure 150 which is shown in FIG. 1(e). This process can be repeated to produce multiple copper or other conductor levels to form a plurality of interconnect or other levels.

Figure 2 shows a schematic view of a CMOS transistor 200 having a metal gate formed from a damascene/CMP process. Transistor 200 is shown following CMP polishing of a gate metal, such as Cu, Pt, Os, Ir, IrO<sub>2</sub>, Ru, RuO<sub>2</sub> or Ta, using a damascene/CMP process analogous to the copper interconnect process discussed above. Transistor 200 includes silicon substrate 201, the transistor having a source 202 and a drain 203. The source 202 and drain 203 have lightly

doped extensions made possible in previous processing by spacer 204 and 205. A gate aperture is provided in field oxide 208 to reach the silicon substrate 201. A thin gate oxide 218 is disposed on top of silicon substrate 201. Barrier layer 212 is then disposed over gate oxide 218 and on the sidewalls of the gate aperture provided by spacers 204 and 205. Gate metal 215 fills the gate aperture volume and is disposed over barrier layer 212.

Whether an interconnect or a gate electrode is formed using CMP, it is important to stop the CMP process soon after the metal layer is fully removed to minimize removal of underlying layers. Since the metal thickness and polishing rates can be non-uniform across the wafer area, it is also helpful for the CMP process to provide a low polishing rate of the underlying layers below the metal, relative to the metal removal rate.

A diagram of a conventional CMP polisher 300 is shown in FIG. 3. The CMP polisher includes a polishing pad 310 disposed on a platen 320 which rotates. A wafer 330 is pressed into direct contact with the polishing pad by a force exerting structure 350. A slurry solution is provided by a slurry feed 340 to wet the polishing pad 310 which chemically and physically interacts with the surface of the wafer 330.

Conventional slurries used for the CMP include a solid abrasive and an oxidizing substance. Typically, CMP polishing slurries contain a plurality of alumina or silica particles suspended in an oxidizing aqueous medium. In FIG. 3, the polishing pad 310 is attached to the top of the rotating platen 320, while the wafer 330 is brought in contact with the pad 310 from the top. The wafer 330 can either be rotated or kept stationary. The wafer 330 can be moved in a circular, elliptical or in a linear manner with respect to the polishing pad 310. The pressure on

the wafer 330 is generally varied from 0.1 psi to 10 psi, and the rotation speed of the platen 320 is generally varied from 5 rpm to 300 rpm.

The polymeric pad 310 supplies the mechanical component of the polishing process. The harder the polymeric pad 310, the higher the shear stress on the surface of the wafer. However the contact area on the surface will decrease when a harder pad is employed in the process. Typical pads which are commonly used include IC1000 CMP pads manufactured by Rodel Corporation, located in Newark, Delaware.

The diameter of the platen wheels 320 can vary from 10 inches to 45 inches, while the size of the wafer can vary from 1 inches to 12 inches in diameter. To maintain a fixed linear velocity, either the angular velocity can be increased or the radius of the wafer from the center can be increased. It is generally important to generate a linear movement of the pad across the wafer.

When polishing a copper/tantalum/insulator based multi-level structure, copper and the tantalum are generally polished by different slurries in separate CMP steps because of significant differences in the mechanical, chemical and electrochemical properties between copper and tantalum. Copper is a very soft and chemically reactive material, whereas common refractory metal based barrier films, such as WN, TiN, Ta, Ta containing alloys and Ta compounds such as Ta<sub>2</sub>O<sub>5</sub>, TaN, as well as Hf and Ru are chemically passive and mechanically hard materials. Thus, the removal rates of copper and refractory metal based films are quite different for a given slurry composition. Accordingly, two-step CMP processes are generally used when circuits include copper and refractory metal based films. The first step polishes the copper surface, while a second step polishes the refractory metal based film.



Slurries designed to polish tantalum containing layers contain abrasives such as alumina, titania and silica, oxidizing agents such as hydrogen peroxide, potassium iodate or potassium ferricyanide, and other optional additives. Aggressive polishing methodologies are generally used to remove the chemically passive and mechanically hard tantalum containing layers. As a result, the generally soft surface layers underlying the tantalum layer, such as SiO<sub>2</sub> or a low K material, can be damaged. For example, scratches can result which can degrade circuit performance and yield and may also degrade reliability of the integrated circuits. Moreover, the use of conventional refractory metal based slurry chemistries are known to result in several other problems, such as surface defects, dishing and erosion problems, and film peeling.

The surface of the refractory metal based film before the CMP process to polish the same generally has numerous surface non-homogenities, that are necessary to remove during polishing. Some important non-homogenities include residual copper patches and dishing and erosion in the copper regions of the exposed surface. Residual copper can be in form of small patches on top of the refractory metal based layer which were not removed during the copper CMP step. Residual copper may either be deliberately left during the copper polishing step or be the result of a non-uniform copper polishing process. For example, U.S. Patent No. 5,985,748 to Watts, et. al. has suggested that the entire copper layer that is disposed on the tantalum containing barrier layer should not be removed during the copper CMP step. Thus, this process leads to a surface having patches of copper disposed on the tantalum containing layer.

The polishing of a refractory metal based surface which has residual copper poses more polishing challenges. If there are copper patches on the surface, the slurry is preferably able to polish copper at a rate comparable to that of the refractory metal based film. Kaufmann et al. in

U.S. Patent Nos. 6,063,306, 5,954,997 and 6,126,853 has suggested that the slurry for tantalum polishing should have a copper to tantalum polishing ratio between 2:1 and most preferably less than about 1:5. Having high polishing rates for copper compared to tantalum is not desirable because a surface morphology defects, such as dishing and erosion, depend on the ratio of the polishing rate of copper to tantalum. With high copper polishing rates, the dishing and erosion of the surface can increase significantly. Even relative low polishing rates of copper not desirable during tantalum polishing because the copper patches will not be removed.

Refractory metal based film polishing can result in dishing and erosion effects. Dishing results in the surface of the central part the metal interconnection being inlaid in a groove formed on the insulating film due to excessively polishing of the central part compared to the periphery. Erosion occurs when the insulating surface around the interconnection is polished. In erosion, both the metal and the insulating areas are depressed, whereas in dishing, the metal lines are depressed compared to refractory metal based film or the underlying insulating film.

Both dishing and erosion defects can already be present in the incoming wafers provided for refractory metal based film polishing. These defects generally result because the slurry used for copper polishing has a higher polishing rate of copper than compared to refractory metal based films, such as tantalum.

For example, the copper to tantalum polishing ratio can vary from 2:1 to as high as 45:1. The high selectivity of copper compared to tantalum or other barrier layer is necessary to stop the polishing process once the copper layer is removed. However, this can lead to substantial dishing of the surface. By using a slurry which has higher polishing rates for copper compared to tantalum, the dishing resulting from copper polishing can increase further.

To reduce the dishing and erosion introduced during refractory metal based film polishing, a slurry which has a lower polishing rate for copper than the refractory metal based film can be used. However, such a slurry has not been used because the refractory metal based films are mechanically hard and chemically passive and are necessarily removed slower than copper when CMP is used.

Refractory metal based film polishing can also result in the loss of the dielectric materials during the polishing process. The underlying dielectric materials are typically doped or undoped silicon dioxide or other low dielectric constant material such as carbon doped silica or certain polymeric materials. After polishing the refractory metal based film, the underlying dielectric layer becomes exposed. The slurry abrasives, such as silica or alumina, are typically hard and abrasive. These abrasives can also cause significant dielectric erosion and surface defects upon the underlying substrate.

The dielectric loss typically increases as the concentration of particles increase in the slurry, and increases for increasingly alkaline pH ( $\text{pH} > 7$  to 12). High dielectric erosion can cause surface non-planarity and loss of global planarization. To reduce the dielectric erosion, Watts has suggested using slurries that do not contain particles or only a low concentration of particles. Watts discloses use of 0.5 wt.% alumina particles in a slurry to polish the tantalum. Reduced particles can be expected to reduce the dielectric loss. However, reduced abrasive particle concentrations are also expected to substantially reduce the tantalum polishing rate.

Refractory metal based film polishing can also result in the introduction of surface defectivity on the final surface. The final surface generally consists of thin copper lines and contact hole plugs within a dielectric matrix. The dielectric is typically doped or undoped silicon

dioxide, or possibly a new low-K dielectric material. The surface defectivity is characterized by scratches on the surface of copper and the insulator, surface roughness due to etching effects, and the presence of particles which can become attached to the surface. As most refractory metal based film slurries contain hard abrasives such as alumina or silica, these particles tend to scratch the surface of the dielectric and copper. To reduce the surface defectivity, the amount of hard abrasives can be reduced, but this problem still persists.

Refractory metal based film polishing can also result in film peeling of underlying layers. The underlying dielectric film is typically soft and may have poor adhesion to its underlying layer which can produce a tendency to peel. With the advent of new low dielectric constant thin films generally being softer than silicon dioxide, film peeling is expected to worsen. Standard slurries, which use hard abrasives such as silica and alumina, can damage, peel and delaminate the dielectric layer quite easily. Besides peeling and delamination of the surface, the hard abrasives can cause scratches, which can also reduce the yield and reliability of devices. To reduce the possibility of peeling, slurries can use softer particles, such as polymers. However, polymer particles are not expected to be effective for removing mechanically hard refractory metal based films, such as tantalum. Thus, the soft particle approach is not practical for polishing refractory metal based films.

Conventional refractory metal based film slurries can also cause destabilization of the slurry abrasives leading to agglomeration. Agglomeration can provide several unwanted effects in the CMP process including the formation of a large number of surface defects, wide variation in the CMP polishing rates and lack of process repeatability.

Thus, several problems need to be resolved for optimum polishing of refractory metal

based films for semiconductor applications. Selectivity of tantalum to copper and dielectric layers is preferably high to limit dishing and erosion, while abrasive particle contact with layers other than the refractory metal based film is preferably avoided.

If CMP process selectivity could be significantly improved, a one step metal/barrier layer (e.g. Cu/Ta) polishing process could be developed. Such a process could replace the current two step process used to first polish the metal and then in a second step polish the barrier layer. A single step metal/barrier process could reduce cycle time, increase yields and result in significant cost savings.

10082010.022202

## SUMMARY OF THE INVENTION

5 A slurry for chemical mechanical polishing (CMP) of a refractory metal based film includes a plurality of composite particles and at least one selective adsorption additive, the composite particles including an inorganic core surrounded by a shell provided by the selective adsorption additive. The selective adsorption additive may comprise one or more surfactants or polymers. The surfactant or polymeric additive is not substantially adsorbed by the refractory metal based film, whereas other films, such as  $\text{SiO}_2$ , or a low K dielectric film substantially adsorb the selective adsorption additive.

10 As used herein, "substantial adsorption" relative to a given layer is defined as a degree of adsorption which results in a CMP polishing rate (for a given slurry and CMP polishing conditions) with the selective adsorption additive which is less than or equal to 1/3 of the CMP layer polishing rate when the slurry does not include the selective adsorption additive. On the other hand, "non-substantial adsorption" relative to a given film is defined as a degree of adsorption corresponding to a CMP polishing rate (for a given slurry and CMP polishing conditions) with the selective adsorption additive being more than 1/3 of the layer polishing rate when the slurry does not include the selective adsorption additive.

15 As both the particles and the dielectric film surface substantially adsorb the selective adsorption additive, the CMP polish rate of the dielectric is substantially reduced in presence of the additive. On the other hand, the polishing rate of the non-substantially absorbed refractory metal based film or the embedded interconnect metal such as copper (or silver) is higher than the polishing rate of the substantially adsorbent dielectric film.



surfactant or with a cationic surfactant with a small amount, preferably being less than 1% of an anionic surfactant.

Examples of preferred cationic based surfactants for silica include cetyl trimethyl ammonium bromide (CTAB), and cetyl trimethyl ammonium chloride (CTAC), its derivatives and chemical equivalents. The carbon chain length in the surfactant molecule is preferably from 8 -20. Other examples of preferred surfactants for silicon dioxide and low K dielectrics include zwitterionic surfactants, such as KETJENLUBE 522®. KETJENLUBE 522® is the current tradename for what had been called DAPRAL GE 202®, now produced by the Akzo Nobel Functional Chemicals Company, Netherlands. This material is a water soluble copolymer of an average molecular weight of approximately 15,000 consisting of  $\alpha$ -olefins and dicarboxylic acids, partially esterified with an ethoxilated alcohol. KETJENLUBE 522® is highly lubricating and dispersing.

For alumina-like surfaces, such as alumina particles or particles coated with an alumina layer, the preferred surfactants are anionic and zwitterionic. Examples of preferred surfactants for alumina like surfaces include sodium dodecyl sulfate (SDS), Triethanolamine lauryl sulfate, ammonium lauryl sulfate and KETJENLUBE 522®. The concentration of the surfactant can be from 0.1 of a bulk critical micelle concentration (CMC) of the solution to 1000 times the CMC. Preferably, the surfactant concentration is from 0.4 of the CMC to 100 times the CMC.

The selective adsorption additive can include at least one polymer. Polymers can be selected from polyethylene oxide (PEO), polyacrylic acid (PAA), polyacrylamide (PAM), polyvinylalcohol (PVA) and polyalkylamine (PAH).

The slurry can include optional additives. Passivating additives can be provided for



inhibiting the oxidation of a copper or silver containing film. Passivating additives can include benzotriazole (BTA), tolyltriazole (TTA), imidazole, thiols, oxalic acid, mercaptans, sodium hexanoate and carboxylic acid. The concentration of the passivating additive is preferably from 1 mm to 1 Mole, and more preferably from 5 mM to 40 mM.

5           The slurry can also include at least one complexing agent. The complexing agent can be acetic acid, citric acid, tartaric acid or succinic acid. The concentration of the complexing agent can be from 1 mM to 1.0 M.

The slurry may include one or more organic solvents to add stability to the micelles. Generally, the combined organic solvent concentration should be no more than about 5% wt of the slurry. Preferred organic solvents include alcohols, such as methyl and ethyl alcohol.

The slurry can also include at least one salt for controlling the strength of the surfactant adsorption. The salt can be selected from a chloride (NaCl or KCl) a nitrate or an ammonium-based salt. Preferred salts are non-alkali salts, such as  $\text{NH}_4\text{Cl}$ ,  $\text{NH}_4\text{NO}_3$ .

The pH of the slurry can be from 6 to 13. Preferably, the pH of the slurry is from 8 to 11.

The slurry preferably includes at least one oxidizer in a concentration of 0.1 to 30 weight % of the slurry. Oxidizers can include hydrogen peroxide, potassium ferrocyanide, potassium iodate and perchlorates. The slurry preferably forms an oxide layer on the refractory metal based film having a thickness preferable being less than about 0.2  $\mu\text{m}$ .

20           The selective adsorption additives can exhibit substantial adsorption to a dielectric film, such as silicon dioxide or silicon nitride, with little or no adsorption to a refractory metal based film or metal gate or interconnect film, such as a copper or silver containing film. The surfactant can also exhibit adsorption to a copper or silver containing film greater than adsorption to the

refractory metal based film.

The selective adsorption additive can exhibit substantial adsorption to the dielectric film, the dielectric film selected from the group consisting of silicon dioxide, silicon nitride and low K materials. The selective adsorption additive can exhibit adsorption to a copper or silver containing film greater than adsorption to the refractory metal based barrier film.

The selectivity of a CMP process using the slurry can be at least approximately 20, at least 50, preferably at least 100, more preferably at least 500, and most preferably at least 1,000 for the refractory metal based barrier film compared to a silicon dioxide or low K film. The term selectivity refers to the CMP polishing rate of the metal film when compared to the dielectric film polishing rate.

The slurry can provide a selectivity of at least 1.0 for the refractory metal based barrier film compared to a film comprising copper or silver. In another embodiment, the slurry can provide a selectivity of at least 2.0 for the refractory metal based barrier film compared to a film comprising copper or silver.

The slurry can provide a selectivity of at least approximately 20, at least 50, preferably at least 100, more preferably at least 500, and most preferably at least 1,000, for a layer comprising copper or silver compared to a silicon dioxide or low K film.

The slurry can provide an adsorption ratio (AR) for a film comprising copper or silver of no more than 3.0, the refractory metal based barrier film of no more than 5, and the dielectric film of at least 10. The AR of a material X, denoted as  $AR_X$ , is defined as the CMP polish rate without surfactant or polymer additive divided by the CMP polish rate in presence of the surfactant or polymer additive. The AR of the dielectric film can be at least 50, is preferably at

least 100, is more preferably at least 250, and is most preferably at least 1000. The particles in the slurry can also be chosen so that the surfactant or polymer adsorption characteristics are similar to the underlying dielectric layer.

5 The slurry can provide an AR for a film comprising copper or silver of no more than 2, the refractory metal based barrier film of no more than 2, and the dielectric film of at least 10. In this embodiment, the AR of the dielectric film is preferably at least 100, more preferably at least 500, and most preferably at least 1000.

The slurry can provide a selective adsorption ratio for a film comprising copper or silver to the refractory metal based barrier film of at least 1.0. Selective adsorption ratios (SARs) are defined herein by comparing the adsorption ratios (ARs) of two materials, such as X and Y. The adsorption selectivity of material X compared to material Y, denoted by  $SAR_{X/Y}$  at a particular concentration "C" of the surfactant or polymer additive is what is expressed by SAR. The slurry can provide a SAR of the dielectric film to the refractory metal based barrier film of at least 10 to 50, preferably at least 100, and more preferably at least 500.

20 A method for chemical mechanical polishing (CMP) a structure including refractory metal based film and a dielectric film includes the steps of providing a slurry including a plurality of composite particles and at least one selective adsorption polymer or surfactant additive, the composite particles including an inorganic core surrounded by a selective adsorption additive shell. The dielectric film substantially adsorbs the selective adsorption additive, while the refractory metal based film does not substantially adsorb the selective adsorption additive. The slurry is applied to the structure. Overburden regions of the refractory metal based film are then removed using a polishing pad, the refractory metal based film generally being first converted

into an oxidized form by the slurry.

5 The slurry can be used to implement a single step chemical mechanical polishing (CMP) process for polishing a structure which includes a gate or interconnect metal film, a refractory metal based barrier film, and a dielectric film. The one step method includes the steps of providing a slurry including a plurality of composite particles and at least one selective adsorption additive, the composite particles including an inorganic core surrounded by a shell including the selective adsorption additive. The refractory metal based barrier film and the gate or interconnect metal film do not substantially adsorb the selective adsorption additive while the dielectric film substantially adsorbs the selective adsorption additive. The slurry is applied to the structure. Initially, overburden regions of the gate or interconnect metal film are removed. Following removal of the overburden regions of the gate or interconnect metal film overburden regions of the refractory based barrier film are removed using a polishing pad with the same slurry resulting in polishing of the gate or interconnect metal film and refractory metal based barrier film in a single, preferably continuous, polishing step.

10 In the single step CMP process, the selectivity of the gate or interconnect metal film to the dielectric film is preferably at least 50, the selectivity of the gate or interconnect metal film to the refractory based barrier film is preferably at least 1.0 and the selectivity of the refractory based barrier film to the dielectric film is preferably at least 50. In a more preferred embodiment, the selectivity of gate or interconnect metal film to the dielectric film is at least 200. The gate or  
20 interconnect metal film can comprise copper or silver, and alloys thereof. The selective adsorbent additive can be a surfactant or a polymer and include one or more optional passivating additives, such as complexing agents, salts and oxidizers as described above.

## BRIEF DESCRIPTION OF THE DRAWINGS

A fuller understanding of the present invention and the features and benefits thereof will be accomplished upon review of the following detailed description together with the accompanying drawings, in which:

5

FIG. 1 shows cross sectional views after various steps in a copper damascene/CMP process.

FIG. 2 is a cross section of a CMOS transistor having a metal gate formed from a damascene/CMP process.

FIG. 3 is a perspective view of a conventional CMP polisher.

FIGs. 4(a), (b) and (c), (d) and (e) illustrate possible configurations of core particles, according to various embodiments of the invention.

FIG. 5(a), 5(b) and 5(c) are TEM photographs of coated core particles.

15 FIGs. 6(a), (b) and (c) are TEM photographs of nanoporous core particles.

FIGs. 7(a), (b) and (c) illustrate some possible shell configurations for composite particles having various surfactant layer structures disposed on silica particles, while FIG. 7(d) shows

selective adsorption of self-assembled surfactant molecules on a silicon dioxide surface, according to embodiments of the invention.

FIG. 8(a) illustrates a schematic diagram showing the variation of adsorption ratio (AR) as a function of concentration for metals and dielectric for two types of dielectrics.

5 FIG. 8(b) is a schematic diagram which shows the variation in selective adsorption ratio (SAR) of dielectrics compared to metals as a function of surfactant concentration.

FIG. 9(a), (b) and (c) illustrate a shelled configuration for a composite particle coated with a selective adsorption additive, composite particle/surface interactions for polishing metal and dielectric layers, respectively, where the selective adsorption additive is substantially adsorbed to the particle and the dielectric, but not the metal layer.

FIG. 10 are force measurements on tantalum, copper and silicon dioxide films in a slurry containing 20 mM BTA and 16 mM C<sub>12</sub>TAB at a pH of 9.

## DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The invention relates to slurries for polishing structures including refractory metal based barrier layers using a chemical-mechanical polishing (CMP) process. The invention may also be used to polish both a gate or interconnect metal layer, such as copper or silver layer and alloys thereof as well as a refractory metal based barrier layer, such as Ta, TaN, WN or TiN in a single polishing step. The gate or interconnect metal layer may be embedded in the refractory metal based layer material.

The slurry is useful for polishing single or multi-level metallization that include, but is not limited to, integrated circuit metallic thin films and multi-level structures. The CMP slurry can also be used in other semiconductor processes where a copper or silver film may be required such as replaceable gate transistors in the front-end device technology, making new types of memory devices such ferroelectric devices including RAMs, high-K DRAM structures, magnetic RAMS (MRAMS), tunneling magnetoresistance devices (TMR), and giant magnetoresistance devices (GMR).

As used herein, the terms copper and copper containing alloys are used interchangeably and can be used to represent structures having gate or interconnect metal layers which have different underlying layers such as Ti/TiN/Cu, Ta/Cu, TaN/Cu, WN/Cu and X/Cu where X is Pt, Ir or W. It should be noted that the invention is also applicable for CMP of metals and metal alloys which share similar mechanical and chemical properties to that of copper and copper alloys, such as silver (Ag) and its alloys. Silver has excellent electrical conductivity and has high electromigration resistance which makes it an ideal candidate for interconnect applications. Silver can also be used as a single or multilayer electrode material in applications involving

CMOS, FeRAM, TMR, and related devices. Thus, in all applications where copper is currently being used or planned for use, it is likely in the future that materials such as silver or its alloys may replace copper. Accordingly, references and examples herein relating to the CMP of copper films should be understood to include CMP of materials which share similar mechanical and chemical properties to that of copper, such as silver and silver alloys.

The term "refractory based barrier layer" is used herein to include elemental refractory metals such as tungsten, titanium, and tantalum, and refractory alloys and compounds, such as Ta<sub>2</sub>O<sub>5</sub>, TaN, TiN and, WN. Such refractory based barrier layer films typically underlying a gate or interconnect metal film, such as a copper containing film, such as a copper/silver containing film, or may embed a copper or silver containing film.

A chemically active slurry for the CMP of a refractory based metal barrier film includes a plurality of composite particles and at least one additive, the additive providing selective adsorption properties. The composite particles include an inorganic core, the inorganic cores coated with the additive, the additive selected to preferentially adsorb to the cores. The selective adsorption additive preferably provides non-substantial adsorption to metal or their associated metal oxide layers and substantial adsorption to underlying dielectric layers, such as SiO<sub>2</sub> or low K dielectric materials.

The selective adsorption additive is selected from suitable surfactants or polymer additives. As a result, the invention can provide abrasive particles that produce high shear stresses on refractory metal based barrier layers, similar or somewhat lower shear stress on gate or interconnect metal layers, such as copper, and extremely low shear stress to the underlying dielectric material. Conventional abrasive particles cannot achieve all these varying shear stress



profiles for the various exposed materials at the same time.

The invention permits refractory metal based barrier film polishing by employing selective particle-surface contact. Specifically, the selective adsorption additive provided in the slurry can form self-assembled coating layers at the particle-liquid interface and the underlying  
5 insulator-liquid interface, but not at the refractory based metal-liquid interface. As a result, there is little or no abrasive contact and resulting removal of the composite particles with the insulating layer.

The CMP slurry for the polishing of refractory based metals provides selective polishing of refractory based metal containing layers with respect to gate or interconnect metals, such as copper, silver or gold, and underlying dielectric layers, such as silicon dioxide or a low K dielectric materials. A wide range of low-K dielectric materials, most having a  $K < 3$ , comprised of both inorganic and organic dielectric films are currently available. These films are generally deposited using either spin-on or CVD processes.

Example of such inorganic materials include doped oxide, such as F-doped as FSG (fluorine silicate glass), H doped as HSQ, C and H doped as MSQ, HOSP, BLACK  
DIAMOND®, Coral® manufactured by the Novellus Corporation, San Jose, Ca. and porous silica, such as aerogels, xerogels and nanoglass. For example, TEOS (tetraethylorthosilicate) FSG (fluorinated silicate glass) is a silicon dioxide based material provided by Applied Materials that has been modified by the introduction of fluorine to lower the capacitance (K-value) of the  
20 dielectric film. Organic polymers can include amorphous fluorocarbon polymers, fluorinated polyimide, PTFE poly(arylene ether), benzocyclobutene, SILK and FLARE.

By reducing the gate or interconnect metal polishing rate the surface planarity of the

wafer can be considerably improved. Preferably, the slurry provides a refractory based metal/gate/interconnect metal selectivity of greater than 1 and a refractory based metal/dielectric selectivity of 20 or higher. The term selectivity refers to the ratio of the polishing rate of one film to another.

5           The invention can also provide a single step polishing process for a metal/barrier layer/dielectric structure, such as Cu/Ta/SiO<sub>2</sub> or Ag/Ta/SiO<sub>2</sub>. A single step process as used herein refers to a polishing which utilizes a single slurry mixture, the single slurry mixture including a chemical mixture along with a fixed concentration of composite particles. The chemical mixture includes at least one selective adsorption additive and can include other optional additives, such as complexing agents and oxidizers.

203220-01023061  
The composite particles include an inorganic core surrounded by a surfactant shell provided by at least one selective adsorption additive, such as a surfactant. The selective adsorption additive is selected so that the layers to be polished, such as a refractory metal based barrier film and gate or interconnect metal do not substantially adsorb the selective adsorption additive, while the selective adsorption additive adsorbs strongly on the underlying dielectric layer, such as SiO<sub>2</sub> or a low K dielectric layer. As used herein, the term "low K dielectric" refers to a dielectric material having a dielectric constant of approximately 4, or less, such as Black Diamond®. This leads to significant polishing of the refractory metal based barrier film and gate or interconnect metal, but no significant polishing of the underlying dielectric layer.

20           In the preferred embodiment of the invention, the slurry particles are selected to have a surface composition that matches the underlying dielectric material. In this preferred embodiment, the surface chemistry for the selective adsorption additive, such as a surfactant, can

be the same with respect to the slurry particles and the underlying dielectric layer.

Matching the surface chemistry of the slurry particles and the dielectric material surface results in repulsion of the slurry particles from the dielectric surface. As a result, the dielectric polishing rate can be very low. For example silica particles are preferably selected if SiO<sub>2</sub> or a doped silica or porous silica is the underlying dielectric material. Alternatively, coated particles can provide matched surface chemistry to that of the underlying dielectric material by using non-silica particles cores, such as alumina coated with silica to produce essentially equal adsorption of the selective adsorption additive on the slurry particles and the dielectric layer. Substantial adsorption of the additive can provide two other functions. It can stabilize the slurry as well as reduce the particle contamination on the wafer surface after completion of the CMP process.

In the case of a tantalum based barrier material, the slurry generally provides an oxidant to oxidize the tantalum (or other refractory metal) to tantalum oxide to ease removal. However, tantalum oxide is a comparatively hard material. Accordingly, conventional soft slurry particles cannot generally remove tantalum oxide or other refractory metal oxides. Typically, to increase the stress on the barrier layer surface to facilitate efficient polishing, silica, alumina, titania or other hard abrasive particles are added to the slurry. It is known that larger sized particles result in larger stresses on surface films, thus being better able to better dislodge the oxide film from the tantalum surface. However, it is known that larger particles generally lead to more scratching.

Larger particles also increase the removal rate of interconnect or gate level metal such as copper, since stress assisted removal of surface layers is the generally the primary CMP removal mechanism. Abrasive particles can also result in rapid removal of the underlying insulating layer (e.g. silicon dioxide or a low K dielectric) once the refractory metal based barrier layer is

polished off. Thus, use of a conventional refractory metal based slurry containing large particles cannot provide the desired results of reduced removal of copper and insulating layers during refractory metal based polishing and limited scratching.

5 Abrasive particle interaction with soft insulating layers, such as silicon dioxide, besides resulting in scratching, can also lead the peeling of insulating film. This problem worsens as the particle hardness increases. Ideally, a barrier layer CMP slurry would provide abrasive particles that produce high shear stresses on refractory based barrier metals and interconnect or gate level metals, such as copper, and extremely low shear stress to the underlying insulating dielectric material. A conventional abrasive particle based CMP process cannot achieve all these varying shear stress profiles for various materials at the same time that a CMP process which utilizes composite particles according to the invention can provide.

The concentration of composite particles is generally from 1 to 40 wt. %. A preferred concentration range for composite particles is between 3 to 20 wt. %.

The inorganic composite particles cores can be selected from at least five different types of particles. The cores can be inorganic single-phase particles, coated (multiphase) core particles, metal particles, mixed composite particles and nano-porous particles, or mixtures thereof. All the particle types can be made from known techniques, such as liquid based processes, gas based processes and dry/wet milling based processes.

20 The primary size of the core particles can vary from 5 nm to 50 microns. The preferred size is between 30 nm to 300 nm. The primary particle size refers to the minimum unaggregated size of the particles. A pictorial representation of cores made up of the five different material types, being inorganic single-phase particle, coated particle, metal particle, mixed composite

particle and nano-porous particle are shown in FIGs. 4(a), (b), (c), (d) and (e), respectively.

The cores of the composite particles can be selected to achieve desired mechanical, surface chemical and selective adsorption additive (surfactant or polymer) adsorption characteristics, respectively. For example, if a particular hardness and surface characteristic is desired, the inorganic core can be composed of a hard core, such as alumina, silicon nitride, and coated with a thin layer, such as silicon dioxide, low K dielectric or a non-soluble polymer, which mimics the composition of the dielectric layer. Thus, particles with specific desired mechanical and additive adsorption properties can be obtained. The mechanical properties of the composite particles are primarily controlled by the properties of the bulk material comprising the core, but the surfactant adsorption properties are controlled by the coated layer on the surface of the core particle.

It may also be possible to change the additive (surfactant or polymer) adsorption site density at surfaces including the surface of the core particle. This can be done by forming a composite core particle from two or more distinct phases or having a nanoporous particle structure. If a hydrophobic surface is desired, a metal or graphite particle or a non-soluble polymeric coating on the core particle can be used.

Single-phase inorganic particle can be selected from materials, such as silica, zirconia, yttria, alumina, titania, silicon nitride, silicon carbide or its mixtures. Multiphase core particles can be particles with an internal composition of either silica, zirconia, alumina, titania, silicon nitride, silicon carbide, ceria and manganese oxide or its mixtures having at least one optional solid coating of a thin layer of a metal, semiconductor or an oxide of these materials. Metal particles can include aluminum, titanium, copper or their alloys, while semiconducting particles

can include silicon. These materials can include a surface thin oxide layer on their surface. The thickness of the coatings can vary from 0.5 nm to 500 nm. Regardless of whether single phase cores or multiphase cores are used, the selective adsorption additive is disposed on the surface of the respective particles.

5           The preferred thickness of the solid coating is between 10 nm to 100 nm. The solid coating can be of zirconia, alumina, titania, silicon nitride, silicon carbide, polymeric materials and its mixture, its composition being different from its internal (core) composition. The coatings can be continuous or discrete and provide 10 to 100% core particle surface area coverage. The coatings preferably have different surfactant characteristics compared to the bulk material comprising the particle.

Nano-porous particles may be particles providing nanosized pores having sizes varying from 0.21 nm to 30 nm in particles, such as silica, alumina and titania. The pore volume can vary from 0% to 80% of the total volume of the porous particles.

Preferred examples of single phase core particles include compositions similar to the underlying dielectric material such as silicon dioxide, doped silicon dioxide, carbon doped silicon dioxide. A preferred single-phase core particle is silica. A preferred multiphase particle is alumina or silica coated with layer with similar composition as the underlying dielectric layer such as silica, low K dielectric layers, doped silica, carbon doped silica, nano-porous silica or a low K dielectric layer. More preferred multiphase core particles include alumina coated with  
20 silica, silica coated with nano-porous silica, and silica coated with cerium oxide.

A preferred example of a two phase composite particle is silica and silicon nitride. A preferred example of a nano-porous particle is silica with porosity varying from 1% to 80% of

the total volume.

Figure 5(a), (b) and (c) show TEM photographs of various coated core particle structures. Figure 5(a) shows an alumina particle coated with silica, while FIGs. 5(b) and 5(c) show examples of a silica particle coated with a nano-porous silica material and silica particle coated with cerium oxide, respectively. All three coatings were formed by wet precipitation techniques. The coating thickness varied from 0.5 nm to 50 nm. By applying a solid coating to form multiphase core particles, both the bulk mechanical properties and the surface adsorption properties of the particles can be tailored.

Nano-porous silica particles can be formed by a modified Stober process (W. Stober, A. Fink, E. Bohn, J. Colloids and Interfacial Science, 26, 62-69 (1968)). The particle size can vary from 200 nm to 500 nm, while the porosity can vary from 10 to 60 %. As the porosity of the surface increase the number of adsorption sites are expected to increase. Figure 6 shows TEM photographs showing different sizes of nanoporous core particles. The particles are mono-dispersed and spherical in nature. It is noted that the aspect ratio of particles can be changed using alternate formation methods.

The selective adsorption additives preferably provide several characteristics. First, the selective adsorption additives should substantially adsorb on the inorganic single or multiphase core particles in the slurry, to form a soft shell with a relatively immobile individual surfactant or polymer additive layer or relatively immobile self assembled structures, such as micelles. Similar adsorption characteristics on the polymer also lead to formation of similar structures. The selective adsorption additive should not substantially adsorb onto the gate or interconnect metal, such as copper, or the refractory metal based barrier layer, such as tantalum.

Preferentially adsorption of the selective adsorption additive to the single phase or multi-phase core particle forms composite particles having a core coated with a soft shell. The hard core layer refers to a hardness greater than 2.0 on Mohs scale, while a soft shell refers to a hardness less than 2.0 on a Mohs scale. To form the hard core-soft shell structure, a selective  
5 adsorption additive selected from surfactants and polymer additives is added to the slurry. The surfactant or the polymer additive is selected to provide specific adsorption characteristics, the adsorption characteristics regulating the polishing characteristics of the slurry.

The surfactant or polymer is preferentially adsorbed to the core particles and the underlying dielectric, such as  $\text{SiO}_2$ , doped  $\text{SiO}_2$ , nanoporous silica, or a low K dielectric material. The surfactant/polymer additive should be not substantially adsorbed to the layers which are to be polished, such as a gate or interconnect metal layer (e.g. copper or silver) and refractory based barrier layers (e.g. Ta).

The adsorbed surface layer disposed on the core particles or the underlying substrate may be in the form of partial layer coverage or in the form of the three-dimensional self assembled layer on the surface. Examples of three-dimensional self-assembled layers include, bilayers, spheres, hemispheres, cylinders, and rods, reverse micellular structures. If used, polymeric additives can attach to the surface can be in the form of coils or in form of flattened or extended structures.

The removal of the generally mechanically hard and chemically passive refractory metal  
20 based barrier layers, such as tantalum, is more easily achieved if the surface of the barrier layer is oxidized to tantalum oxide. For example, tantalum oxide can more easily be readily removed compared to metallic tantalum by CMP processing.



5 The chemicals for oxidizing the refractory metal based barrier layer and metal films can be standard oxidizers, such as hydrogen peroxide. Examples of other oxidizers include potassium ferrocyanide, potassium iodate and related oxidizers, such as perchlorates. The concentration of oxidizers preferably is from 0.1 to 30 wt. %. Under these conditions, both the refractory based metal, such as tantalum, and interconnect or gate metal, such as copper, form respective oxide layers.

It is generally preferable for the slurry to produce a barrier layer oxide layer thickness of from approximately 1 to 200 nm. To limit the thickness of the oxide layer formed, oxidation inhibitors can be added to the slurry, such as BTA. If the oxide layer is too thin, the CMP removal rate will generally be too low.

As copper or other metal lines are generally present on the wafer, there may be a need to passivate the metal (e.g. copper) lines during CMP process. If the barrier layer (e.g. Ta) polishing rate is reduced, then the selectivity of the barrier layer polishing process will also decrease. The lack of a surface modified layer may also create scratches on the surface. Thus, defectivity can be expected to increase. If the oxide thickness is generally greater than 200 nm, the planarity of the process can be compromised. Good planarity can reduce the surface defectivity such as dishing and erosion.

20 Both dishing and erosion defects are generally present on the incoming wafers which arrive for barrier layer polishing. Incoming wafers have defects because the slurry used for metal CMP, such as copper CMP generally has a higher polishing rate for the metal as compared to the barrier layer. To reduce the dishing and erosion, a barrier layer CMP slurry preferably has a lower polishing rate for metals, such as copper, as compared to barrier layers, such as tantalum.

5 The pH of the slurry can also play a significant role in barrier layer CMP characteristics. For example, the pH under which both tantalum and copper form oxide layers is between approximately 6 to 13. Preferably, the pH is held between 8 to 11 because of enhanced adsorption of surfactants or polymer additives on silicon dioxide and the stability of the slurry in a neutral to alkaline pH.

It is also desirable to ensure that the slurry particles are stable in a colloidal suspension in the normally high ionic strength slurry. This can be difficult because the high ionic strength of the slurry can shield the electrostatic charges in slurry, which are critical in maintaining the slurry stability. The theory of Derjaguin, Landau, Verwey and Overbeek (DLVO theory) predicts suspension stability when the surface charge of the particles are high and the formation and overlap of the electric double layer between two particles prevents agglomeration of the particles. However, the presence of salts in high ionic strengths can screen the surface charges and destabilize the slurry. The substantial adsorption of the surfactant/polymer additives onto the dielectric layers and the inorganic core particles helps maintain the stability of the slurry.

To be able to achieve the wide range of variability in the particle interactions with different layers for refractory metal based film polishing, the invention provides a slurry including a plurality of composite particles, the composite particles comprising core abrasive particles surrounded by a soft shell of a self-assembled surfactant or polymer layer. In the case of surfactants, self-assembled surfactant layers can be in the form of aggregates, known as micelles.

20 The shape of the micelles can vary from cylindrical, spherical, bilayer, hemispherical or other shapes, depending on factors such as the nature of the interaction with the wafer surface, the concentration of surfactant, the presence of ions, and the nature of the head and tail group of

the surfactants. Figures 7(a), (b) and (c) show some possible configurations of composite particles suitable for use in a slurry, the composite particles having various surfactant layer structures disposed on silica particles. In each configuration shown, the silica particles are surrounded by a surfactant shell.

5           Figure 7(d) illustrates selective adsorption of surfactant particles shown in FIG. 7(c) on a silicon dioxide surface, but not on a tantalum or a copper surface. Selective adsorption permits selective polishing of layers which do not substantially adsorb the surfactant (Cu, Ta) while not substantially polishing the silicon dioxide surface.

The surfactants or polymers preferably provide selective adsorption characteristics on different surfaces exposed to the slurry. For example, the surfactant or polymer preferably provides strong adsorption to the slurry particles and underlying insulating dielectric layers, such as silicon dioxide. The formation of a selective highly adsorbed layer on the slurry particles and the dielectric surface leads to several helpful properties.

Slurry stability can be improved by the surfactant because the surfactant or polymer coated particles repel one another and as a result tend not to agglomerate. This repulsion is due to steric forces. The dielectric layer remains substantially unchanged by the refractory metal polishing process because there is essentially no particle-surface contact at the dielectric surface. As a result, there is little or no scratching or peeling of the dielectric layer. The dielectric surface may also be cleaned during barrier layer polishing due to repulsion of particles from the dielectric surface. Thus, the formation of the composite particles having a hard core and soft additive shell and strongly adsorbed surfactant layer on insulating surfaces results in improved CMP barrier layer results.

10022010-0222001  
2022010-0222001

To ensure that the composite hard core-soft shell particles are optimized for CMP polishing of refractory based barrier layers on circuits for applications when copper films are present, it is preferable to provide high polishing rates for refractory metal based barrier layer relative to the polishing rate for copper or other metal. This can be achieved by providing composite slurry particles coated having a surfactant or polymer coating, where the refractory metal based barrier layer film adsorbs little or no surfactant, while the copper or other metal layer adsorbs more surfactant as compared to the tantalum film. Thus, an additive which provides substantial adsorption on the underlying dielectric surface, some adsorption on the copper or other metal film surface and little or no adsorption on the refractory metal based barrier layer film can be used to provide an optimized barrier layer polishing process.

A variety of surfactants which can be used with the invention. Surfactants can either be cationic, anionic, zwitterionic or non-ionic. The surfactants can be used individually or in a mixed state. A list of surfactants which can be used with the invention is provided in a book by M. J. Rosen, Surfactants and Interfacial Phenomena, John Wiley & Sons, 1989, hereinafter Rosen, on pgs. 3-32, 52-54, 70-80, 122-132, and 398-401.

Surfactants are generally characterized by a hydrophilic head group and a hydrophobic tail group. Examples of tail groups include straight chain, long alkyl groups (carbon chain length varies from  $C_8$  to  $C_{20}$ ), branched chains, long chain ( $C_8$ - $C_{15}$ ) alkylbenzene residues, long chain perfluoroalkyl groups, polysiloxane groups, high molecular weight propylene oxide polymers.

Examples of anionic surfactants include carboxylic acid salts, amine salts, acylated polypeptides, sulfonic salts, higher alkylbenzene sulfonates, secondary n-alkanesulfonates, sodium alkene sulfate (SAS), sodium dodecyl sulfate (SDS), olefin sulfonates (AOS), sulfosuccinate

esters, sulfated linear primary alcohols, sulfuric acid ester salts, phosphoric amides, polyphosphoric acid esters and perfluorinated anionics. Preferred anionic surfactants include SDS and SAS and their alkali free derivatives.

5 Examples of cationic surfactants include long chain amines and their salts, diamines and polyamines and their salts, quaternary ammonium salts, polyoxyethylenated (POE) long chain amines, quaterized polyoxyethylenated long chain amines, amine oxides and cetyl trimethyl ammonium (CTAB). Preferred cationic surfactants include dodecyl trimethylammonium bromide ( $C_{12}$ TAB) and related compounds, such as  $C_8$ TAB,  $C_{10}$ TAB,  $C_{14}$ TAB,  $C_{16}$ TAB,  $C_{18}$ TAB, with varying hydrophobic chain lengths. Other preferred examples of cationic surfactants include dodecylammonium chloride, cetylpyridium bromide. In each of these cases, the hydrophobic chain length is preferably varied from  $C_8$  to  $C_{20}$ .

Examples of zwitterionics include B-N alkylaminopropionic acids, N alkyl-B. iminodipropionic acids, imidazoline carboxylates, N-alkylbetanines, amine oxides, sulfobetaines and DAPRAL<sup>®</sup> variants. A preferred zwitterionic surfactant is KETJENLUBE 522<sup>®</sup>.

20 Examples of non-ionic surfactants include polyoxyethylenated alkylphenols, alkylphenol, polyoxyethylenated straight chain alcohols, polyoxyethylenated polyoxypropylene glycols, polyoxyethylenated mercaptans, long chain carboxylic acid esters polyoxyethylenated silicones, tertiary acetylenic glycols and TRITON X-100<sup>®</sup> manufactured by the Dow Chemical Corporation, MI. TRITON X-100<sup>®</sup> is octylphenol ethylene oxide condensate and is also referred to as Octoxynol-9. This material has a molecular weight of 625 amu.

Preferred examples of non-ionic surfactants include TWEEN-80<sup>®</sup> and the family of TRITON X<sup>®</sup> compounds. TWEEN-80<sup>™</sup> is manufactured by the ICI group of Companies,

NewCastle, DE. TWEEN 80® is polyoxyethylene sorbitan monooleate, and has the following synonyms: TWEEN 80®1, polyoxyethylene sorbitol ester; polysorbate 80 and PEG (20) sorbitan monooleate. This material has the molecular formula  $C_{64}H_{124}O_{263}$  and a corresponding molecular weight of 13103 amu.

5           A preferred embodiment of the invention uses silica or silica inorganic cores coated with surfactants to form a hard core-soft shell structure. The inorganic core can be silica, doped silica, porous silica, or hard particle (Mohs hardness greater than 3.0) coated with silica, doped silica, or a porous silica layer. For silica/nanoporous or silica/nanoporous silica coated inorganic cores the preferred surfactant is cataionic, zwitterionic, or a mixture of cationic/non-ionic surfactant or with a cationic surfactant with generally less than 1% of an anionic additive. Examples of preferred cationic based surfactants for silicon dioxide include CTAB, and CTAC, and their derivatives and chemical equivalents. The carbon chain length in the surfactant molecule is preferably from 8 to 20. Other examples of preferred surfactants for silicon dioxide include zwitterionic surfactants, such as KETJENLUBE 522®. The concentration of the surfactant can be from 0.1 of a bulk critical micelle concentration (CMC) of the solution to 1000 times CMC. Preferably, the surfactant concentration is from 0.4 of the CMC to 100 times CMC. The bulk CMC value of the surfactant is defined as the minimum concentration at which the surfactant self assembles to form structured layers in a bulk solution.

20           In each of these surfactants, the head group and the tail group can be varied to provide similar effects in the slurry but at different concentration levels. In certain cases it may be advantageous to use mixed surfactants to control the adsorption density, the strength of the surfactant adsorption. Examples of some possible synergistic effects are given on pg. 398-401 of

Rosen. Additionally some salts as outlined earlier may be added which control the strength of the surfactant adsorption.

Organic solvents may be added to the slurry to add stability to the micelles. Generally, the organic solvent should be no more than about 5% wt of the slurry. Preferred organic solvents include alcohols, such as methyl and ethyl alcohol.

The surfactant additives described above can be supplanted or used in combination with polymeric additives such as polyethylene oxide (PEO), polyacrylic acid (PAA), polyacryamide (PAM), polyvinylalcohol (PVA), polyalkylamine (PAH) and related polymeric compounds. These polymer additives can be used as dispersants for particles in the slurry. The molecular weight of these additives can be varying from 500 to 100,000 amu. The concentration of these additives can vary from 1 mg/liter to 10 g/liter.

Polymeric additives are generally chosen based on the nature of the surface sites for polymeric adsorption. For example if silica surface based slurry particle cores are used, the preferred choice of additives are PEO, and PVA. If silicon nitride slurry particle cores are used, then preferred polymer additive is PAA, which generally strongly adsorb to the silicon nitride cores. For the metal layers such as copper, tantalum and silver, several mercaptans, and thiol based compounds can be readily adsorbed to these surfaces and can be readily used to modulate the polishing characteristics.

Additionally, some salts may be added to control the strength of the surfactant adsorption. In some of these examples, hydrophilic head groups contain alkali metals such as Na and K. However, it may be possible to replace the alkali metals with other ions (such as ammonium based) which may be more compatible with semiconductor processing.

The concentration of surfactants used depends on the type of the surfactant used, the surfaces of particles and wafers such as copper, tantalum, silicon oxide, low K dielectric which the slurry is contact with, and CMC value of the surfactant. At low concentration, the surfactant may adsorb onto the solid surfaces in a patchy manner and change the electrostatic properties and the surface energy of the surface. The adsorption of the surfactant may reduce the etching of the surface layer. At higher concentration of the surfactant, the surfactant molecules may coalesce together to form self assembled structures.

Examples of structured surfactants can include spheres, cylindrical rods, bi-layers, disks and vesicles. Once the bulk CMC is reached, the surface tension of the solution does not generally decrease further, but is accompanied by a rapid drop in the electrical conductivity of the bulk solution. The formation of micelles is thought to be due to the reduction in the free energy of the solution.

The adsorption of surfactant and its self assembly can be measured by a combination of several techniques including Fourier transform infrared spectroscopy (FTIR), adsorption density measurement via solution the depletion method, contact angle measurements and surface force measurements via atomic force microscopy (AFM). The confirmation of micelles at the surface and the bulk of the solution can be investigated using FTIR, AFM, and electrical conductivity and surface tension/contact angle measurements.

The concentration of the surface-active selective adsorption additives is generally provided such that the surfactants are strongly adsorbed to the surface of the particle cores and the underlying dielectric. The concentration in which the micelles form in the bulk of the materials (CMC) varies with the hydrophobic tail and hydrophilic head groups of the surfactant,



and presence of the other additives in the solution. The strength of the surfactant adsorption on the surface of the particle or the dielectric surface depends on the density and the nature of adsorption sites on the surface and the chemistry of the solutions.

If polymer additives are used, the concentration of the polymer additives preferably varies from 1 mg/liter to 2 gm/liter of solution. A preferred concentration of the polymeric additives varies from 10 mg/liter to 1 gm/liter. The molecular weight of the polymeric additive can vary from 500 to 100,000 amu. The preferred molecular weight of the additive varies between 1000 to 10,000 amu.

The surfactants or polymeric additives can exhibit substantial adsorption to the dielectric film such as silicon dioxide or silicon nitride or low K dielectrics such as doped silica, nanoporous silica and certain polymers, and little or no adsorption to the gate or interconnect metal layer and the refractory based barrier layer. The surfactant film can also exhibit adsorption to the gate or interconnect metal layer greater than the adsorption to the refractory based barrier layer, such as a tantalum containing film. As a result, the CMP rate of the tantalum film can be higher than the copper film. The CMP rate of both the metal films should be much higher than the dielectric polish rate due to the selective adsorption characteristics.

To quantify the selective adsorption characteristics of surfactants or polymers additives, this application will define certain new terminology in relation to new measurement techniques. Standard measurement techniques and measures of adsorption density of surfactants use solution depletion methods, contact angle or zeta potential or atomic force microscopy (AFM) methods. These conventional methods have been found to be inadequate to describe the effects of adsorption phenomena on resulting CMP characteristics. Some of the shortcomings of

conventional measurement methods include the inability to conduct measurements in actual CMP conditions where interactive effects may play a critical role. Moreover, conventional methods produce results which generally lack correlation with the CMP polishing rate. As described below, new variables have been defined herein, such as adsorption ratios (AR) and selective adsorption ratios (SAR) to correspond to parameters measured when using the new measurement techniques:

The adsorption and the selective adsorption characteristics of surfactants and polymer additives on various surfaces when immersed in a slurry can be defined by the adsorption ratios (AR) and selective adsorption ratios (SAR), respectively. The adsorption ratio of a material X is denoted as  $AR_X$  and is defined as the CMP polish rate without surfactant or polymer additive divided by the CMP polish rate in presence of the surfactant or polymer additive. The AR is generally always greater than or equal to 1, since the polishing rate of a given material can only generally decrease upon the addition of a surfactant or a polymer additive which exhibits surfactant-like properties. In cases where the surfactant destabilizes slurry, the AR values can be less than 1.0.

$$AR_X(C) = (\text{CMP Polish Rate without surfactant}) / (\text{CMP Polish Rate with surfactant}).$$

Where C corresponds to the concentration of the surfactant or polymer additive. The AR parameter also permits an objective definition of what constitutes substantial adsorption of an additive in relation to one or more layers. As noted earlier, "substantial adsorption" relative to a given layer refers to a CMP polishing rate (for a given slurry and CMP polishing conditions) with

the selective adsorption additive being less than or equal to 1/3 of the CMP layer polishing rate when the slurry does not include the selective adsorption additive. This can be equivalently stated as a CMP polishing rate without the selective adsorption additive being at least three (3) times the CMP polishing rate with the selective adsorption additive.

5           In the case of strong adsorption of the selective adsorption additive, such as by a dielectric layer, AR values can be at least 50, preferably greater than 100, and even 1,000 or more in certain embodiments. This condition typically occurs when the adsorption additive show substantial adsorption to both the dielectric and the inorganic core particle. On the other hand, non-substantial adsorption relative to a given film refers to a CMP polishing rate (for a given slurry and CMP polishing conditions) without the selective adsorption additive being less than or equal to three (3) times the polishing rate of the layer with the selective adsorption additive.

Figure 8(a) shows data for the variation in adsorption ratios as a function of surfactant concentration for dielectrics such as SiO<sub>2</sub>, doped SiO<sub>2</sub> (Type I dielectric) and low K materials such nanoporous silica and polymers such SILK®, FLARE® (Type II dielectric) as well as for gate or interconnect metal layers and refractory based barrier layers (metals). The diagrams reflect the general trend in adsorption ratios for different type additives, such as surfactants and polymers.

As seen in FIG. 8(a), AR values do not change linearly with concentration, but in a rather complicated manner. The complicated nature may be due to different phenomena which occur on the particle as well as the polishing surfaces, and as the concentration of the surfactants or polymer additives are varied. For example, AR value can decrease with addition of additives (point A) due to destabilization of particles in the slurry due to partial adsorption.

The AR ratios may increase rather suddenly with slight increase in concentration as shown (point B) due to formation of micelles and fixation of micelles on the surface of solid surfaces. In other cases, such as point C, the change in AR is basically linear in nature signifying a linear- like effect, such as a linear increase in surface coverage.

5 As the AR increases, a higher adsorption of the additive on the surface of the film or on the particle surface generally results. Besides the accompanying change in the CMP polishing rate, the AR ratio can also be used as a guide to determine other properties of the slurry. Generally, the higher the value of AR, the higher the stability of the slurry. Thus, particle contamination on the surface of a dielectric after CMP polishing can generally be kept at a minimum through the use of surfactant or polymer additives. The other salient aspects of particle defectivity including, scratches and dents, will also generally decrease with increasing AR values. In addition, the planarity of the metal and dielectric polish generally improves with increasing AR values. Besides enhancing the selectivity of the polish, higher AR values are expected to lead to other beneficial properties including slurry stability, reduced surface defectivity of the dielectric and enhanced planarity of polishing.

10  
15  
20 Preferably, surfactants or polymer additives are added to the slurry solution such that the AR values of the underlying dielectric is kept large, typically greater 100, while the AR values of the metal is typically kept generally below about 5.0. This large difference in AR generally occurs above a particular concentration (critical) of the selective adsorption additive. High AR for the dielectric layer relative to the metal layers insures that the polishing rate of the dielectric is much lower than the metal layers.  $C_{critical}$  also defines the minimum concentration of surfactant needed to achieve optimum polishing.  $C_{critical}$  is dependant on the type of surfaces,

nature of the particle core of the core-shell particles and presence of other optional additives which may be included in the slurry.  $C_{critical}$  values have been found to generally vary from 10 % of bulk CMC to over 100 times the bulk CMC value of the surfactant. In case of the polymer additive, no CMC value exists, however the concentration is typically greater than 1 gm/liter.

5 Using specific surfactants and polymer additives, values of  $AR_{Ta}$  were found to vary from 0.5 to 5.0,  $AR_{Dielectric}$  was found to vary from 0.5 to over 10,000, while the AR values for copper and silver were found to vary from 0.5 to 5.0. Accordingly, a slurry can be configured to produce high  $AR_{Dielectric}$  values to permit high metal polishing rates relative to the dielectric.

10 Selective adsorption ratios (SARs) compare the adsorption ratios of two materials, such as X and Y. The adsorption selectivity of material X compared to material Y, denoted by  $SAR_{XY}$  at a particular concentration "C" of the surfactant or polymer additive is defined as the value of  $AR_X$  divided by the value of  $AR_Y$ :

$$SAR_{XY}(C) = AR_X(C) / AR_Y(C)$$

15 Both  $AR_X(C)$  and  $SAR_{XY}(C)$  are generally a function of the type and the concentration (C) of the surfactant or polymeric selective adsorption additive. The higher the SAR, the higher the selectivity of additive adsorption. If Y is a metal, such as Ta, Cu or Ag or alloy thereof, while X is a dielectric such as silicon dioxide or a low K dielectric, to achieve high  $SAR_{Dielectric/metal}$  values it is necessary to have high values of  $AR_{Dielectric}$  and low values of  $AR_{metal}$ . Thus, the selective adsorption additive is preferably selectively adsorbed by the dielectric to  
20 achieve high  $SAR_{Dielectric/metal}$  values. In experiments performed,  $SAR_{Dielectric/Ta}$ ,  $SAR_{Dielectric/Cu}$ ,

SAR<sub>Dielectric/Ag</sub> were found to vary from 1.0 to over 4,000. The SAR<sub>Ta/Cu</sub> was found to vary from 0.3 to 2.0.

Figure 8(b) is a schematic diagram which shows the variation in selective adsorption ratio (SAR) of dielectrics compared to metals as a function of surfactant concentration. Figure 8(b) is derived through point by point calculation ( $SAR_{X/Y}(C) = AR_X(C) / AR_Y(C)$ ) from data provided in FIG. 8(a). As noted above, Type 1 dielectrics include SiO<sub>2</sub>, doped SiO<sub>2</sub>, while Type II dielectrics include low K materials such nanoporous silica and polymers such SILK®, FLARE®.

The selectivity of CMP polishing of material X divided by the CMP polish rate of material Y at a concentration "C" of the surfactant or polymer additive is denoted herein as  $S_{X/Y}(C)$ , and can be expressed by the following equation:

$$S_{X/Y}(C) = SAR_{Y/X}(C) \times S_{X/Y}(0)$$

Where  $S_{X/Y}(0)$  is the ratio of the CMP polish rates of material X and Y when no polymeric or surfactant selective adsorption additives are added to the solution. It is noted that  $SAR_{Y/X}(C) = 1 / SAR_{X/Y}(C)$ . This equation shows that to achieve high selectivity the additive should generally be chosen so that the SAR values and the selectivity at zero concentration should be maximized. The equation for copper/ dielectric, tantalum/dielectric selectivity, silver/ dielectric selectivity can be represented as shown below:

$$S_{Cu/Dielectric}(C) = SAR_{Dielectric/Cu}(C) \times S_{Cu/Dielectric}(0)$$

$$S_{Ta/Dielectric}(C) = SAR_{Dielectric/Ta}(C) \times S_{Ta/Dielectric}(0)$$

$$S_{Ag/Dielectric}(C) = SAR_{Dielectric/Ag}(C) \times S_{Ag/Dielectric}(0)$$

$$S_{Cu/Ta}(C) = SAR_{Ta/Cu}(C) \times S_{Cu/Ta}(0)$$

$$S_{Ag/Ta}(C) = SAR_{Ag/Cu}(C) \times S_{Ag/Ta}(0)$$

5 Thus, to remove a tantalum barrier layer for example, the  $S_{Cu/Dielectric}(C)$ ,  $S_{Ta/Dielectric}(C)$  values should preferably be kept high, such as at least 50 to 100, while the  $S_{Cu/Ta}(C)$  should preferably be kept less than 5.0. These parameters have similar values if copper is replaced by silver. It should be noted that Ta is a representative example for most refractory metal comprising layers.

10 Figure 9(a) shows a schematic of a shelled configuration for a composite particle coated with a selective adsorption additive. Figures 9(b) and (c) shows the interaction of the particle shown in FIG. 9(a) with metal (Cu or Ta) and a dielectric layer ( $SiO_2$  or a low k dielectric). The surfactant or polymer additive is chosen to strongly adsorb to the core particles (FIG. 9(a)) and the underlying dielectric layer (FIG. 9(c)), and to weakly adsorb to Cu and Ta (or other refractory metal based layer). Thus, the surfactant preferably possesses a large AR value for the dielectric and low AR values for the respective metal layers. This also results in a large SAR of metals compared to the dielectric. As a result, a polishing process using the particles shown can provide a high metal to dielectric selectivity.

20 During CMP polishing, the weakly adhered selective adsorption additive layer on the metal are generally removed by the applied pad pressure, while the strongly adsorbed layers on the slurry particles and the dielectric layer are generally not removed. This results in a high

polishing rate for the metal and a low polishing rate for the dielectric. Experiments performed which used varying selective adsorption additives demonstrated a selectivity of a gate or interconnect metal layers such as Cu and Ag and refractory based metal layers, such as Ta from 10 to greater than 1000 relative to silicon dioxide.

5           Passivating chemicals can be added to the slurry along with the selective adsorption additive to further inhibit the oxidation of gate or interconnect metal layer metals and to enhance the surface finish of the gate or interconnect metal layer while not substantially affecting the removal rates of the refractory metal based barrier layer film or dielectric film, such as silicon dioxide. As a result, the polishing rate of a gate or interconnect metal layer, such as copper, can be selectively reduced.

Some of the passivating additives, sometimes referred to as inhibitors, include surfactants and mercaptan based chemicals. For example, passivating additives for copper include benzotriazole (BTA), tolyltriazole (TTA), imidazole, thiols, mercaptans, oxalic acid, sodium hexanoate, carboxylic acid, and their derivatives.

The preferred passivating additives are BTA, TTA, imidazole and mercaptans. For example, the preferred concentration of additives, such as BTA, can be from 1 mM to 1 Mole, while a more preferred passivating additive concentration is from 5 mM to 40 mM.

20           The concentration of oxidant can also be used to control the refractory metal based CMP process. Common oxidants suitable for use with the invention include hydrogen peroxide, potassium iodate, potassium ferricyanide and perchlorate. The oxidant concentration is generally from 1 to 30 wt. %. A preferred oxidant concentration is from 2 to 5 wt. % .

The refractory metal polishing rate, such as the Ta polishing rate, generally decreases for



relatively high oxidant concentrations. For example, high oxidant concentrations result in a low Ta removal rate because oxidants enhance the formation of tantalum oxide on the tantalum surface. Tantalum oxide is harder and more chemically passive compared to tantalum. Thus, the concentration of an oxidizing agent can be used to control the tantalum CMP process.

5           Complexing agents can also be added to the refractory metal based slurry to selectively increase the refractory based metal barrier layer removal rate. Preferred complexing agents can increase the refractory based metal barrier layer removal rate without altering the gate or interconnect metal layer or silicon dioxide removal rate. Examples of complexing agents include nitric acid, acetic acid, sulfuric acid, hydroxy acid, carboxylic acid, citric acid, malic acid, malonic acid, succinic acid, phthalic acid, tartaric acid, dihydroxysuccinic acid, lactic acid, malic acid, fumaric acid, adipic acid, maleic acid, glutaric acid, oxalic acid, benzoic acid, propionic acid, butyric acid and valeric acid.

205220-0109001  
Generally, comparatively weak complexing agents are preferably used. Preferred complexing agents include citric acid, acetic acid, tartaric acid and acetic acid. The concentration of the complexing agent can be from approximately 0.1 mM to 0.5 M. The preferred concentration of complexing agents is from 0.02 M to 0.2 M.

20           The slurry can also include salts. Salts, such as chlorides, nitrates and ammonium-based salts, may be added to further increase the stability of the selective adsorption additive. For example, KI, KBr, KCO<sub>3</sub>, NH<sub>4</sub>I, KCl, NH<sub>4</sub>NO<sub>3</sub> and NH<sub>4</sub>Cl may be used. However, non-alkali containing salts, such as NH<sub>4</sub>Cl and NH<sub>4</sub>NO<sub>3</sub> are generally preferred. The concentration of salt can be 0.1 mM to 0.5 M. A preferred concentration of salt is from 1 mM to 50 mM.

Polishing pressure can affect CMP removal rates for refractory metal based, copper,

10002010-022001  
10002010-022001  
5 silver and silicon dioxide films. Polishing pad pressure is generally set to a pressure from 0.5 psi to 10 psi. Preferably, the polishing pressure range is 2.7 psi to 9 psi. Increasing polishing pressure can be used to increase the refractory metal based barrier layer removal rate, while not significantly affecting removal rates for the interconnect or gate level metal and underlying dielectric layer. For example, copper and silicon dioxide removal rates may remain constant as the polishing pressure is varied due to the formation of a Cu passivated layer such as Cu-BTA, and the selective adsorption of surfactant (e.g.  $C_{12}$ TAB) on the silicon dioxide surface and the surface of the slurry particles. Thus, pressure can be used to optimize the removal rate of refractory metal based barrier layer films as well as improve the refractory metal based barrier layer selectivity to materials such as Cu and silicon dioxide.

Other additives may be included in the slurry. For example, in the case of a copper or silver interconnect or gate layer, the slurry can provide, either directly or indirectly, a reagent for reacting with the copper or silver film to form a soft layer on the surface of the copper or silver film. The soft layer has a hardness less than copper or silver oxide. For example, in conventional copper CMP, cuprite ( $Cu_2O$ ) and/or copper II oxide ( $CuO$ ) are formed on the copper surface. Cuprite or copper II oxide have a hardness, such as measured on the Mohs scale, which is greater than that of copper.

20 Chemical for forming soft layers on the copper or silver surface include iodine, bromine, fluorine, sulfuric acid, hydrochloric acid or carbonic acid or salts, such as KBr or KI. In the case of a copper film, the soft layer can be copper bromide, copper fluoride, copper chloride, copper carbonate, copper sulfate or copper nitrate or any these layers mixed with an oxide layer.

The invention can also be used as a single step polishing process for a metal/barrier

layer/dielectric structure, such as Cu/Ta/SiO<sub>2</sub> or Ag/Ta/SiO<sub>2</sub>. A single step process as used herein refers to a polishing which utilizes a single slurry mixture, the single slurry mixture including a chemical mixture along with a fixed concentration of composite particles.

5 The single step CMP process polishes a structure which includes a gate or interconnect metal film, a refractory metal based barrier film and a dielectric film. The single step process includes the steps of providing a slurry including a plurality of composite particles and at least one selective adsorption additive, the composite particles including an inorganic core surrounded by a shell including the selective adsorption additive. The gate or interconnect metal film can comprise copper or silver, and alloys thereof.

10 The refractory metal based barrier film and the gate or interconnect metal film do not substantially adsorb the selective adsorption additive, while the dielectric film does substantially adsorb the selective adsorption additive. The slurry is applied to the structure. Overburden regions of the gate or interconnect metal film are removed and then overburden regions of the refractory based barrier film are removed by the polishing pad in a single polishing step that can be continuous.

15 The selectivity of the gate or interconnect metal film to the dielectric film can be at least 100, the selectivity of the gate or interconnect metal film to the refractory based barrier film is at least 1 and the selectivity of the refractory based barrier film to the dielectric film is at least 100. The selectivity of the gate or interconnect metal film to the dielectric film is preferably at least  
20 100.

The inorganic cores are preferably multiphase particles, the multiphase particles comprising a first material coated with at least one other material. The surface of the inorganic

core can be selected to be chemically equivalent to the dielectric layer.

The slurry for the single step process can include at least one passivating additive for inhibiting the oxidation of a copper or silver containing film, such as benzotriazole (BTA), tolytriazole (TTA), imidazole, thiols, mercaptans, oxalic acid, sodium hexanoate and carboxylic acid. The concentration of the passivating additive is preferably from 1 mM to 1 Mole.

Complexing agents can also be used, such as acetic acid, citric acid, tartaric acid and succinic acid. The pH of the slurry is preferably from 6 to 13.

The selective adsorption additive can be one or more non-ionic, anionic, cationic or zwitterionic surfactants. For example, the selective adsorption additive can be SAS, SDS, CTAB (e.g. C<sub>12</sub>TAB), TRITON X-100<sup>®</sup> and TWEEN-80<sup>®</sup>, and KETJENLUBE 522<sup>®</sup>. The concentration of surfactant can be from 0.1 of a bulk CMC of the solution to 1000 of the CMC. In one embodiment, the selective adsorption additive comprises CTAB or CTAC, and the inorganic cores comprise silica.

The selective adsorption additive can be at least one polymer. For example, the polymer can be polyethylene oxide (PEO), polyacrylic acid (PAA), polyacryamide (PAM), polyvinylalcohol (PVA) or polyalkylamine (PAH).

The slurry can also include at least one salt, such as chlorides, nitrates and ammonium-based salts and at least one oxidizer, such as hydrogen peroxide, potassium ferrocyanide, potassium iodate, or a perchlorate. Preferred salts are non-alkali containing salts, such as NH<sub>4</sub>Cl and NH<sub>4</sub>NO<sub>3</sub>.

## EXAMPLES

### Example 1: AFM measurement to demonstrate surfactant adsorption selectivity

5 This Example shows the force between a silica particle and tantalum, copper and silicon dioxide films using atomic force microscopy (AFM). Figure 10 shows force measurements on tantalum, copper and silicon dioxide substrates in a slurry solution including 20 mM Benzotriazole (BTA) and 16 mM dodecyltrimethylammonium bromide ( $C_{12}TAB$ ) and silica particles, the solution having a pH of 9. CTAB and BTA can both function as surfactants. The results show that the separation distance (plotted on the x-axis) of the silica particles and the  $SiO_2$  substrate surface is changed by adding BTA and  $C_{12}TAB$ . Specifically, the silica-silicon dioxide interaction shows higher force and long interaction distance than silica/Ta or silica/Cu. This result evidences the highly selective adsorption of surfactant on the silicon dioxide and silica particle surfaces.

10  
15  
20  
25  
30  
35  
40  
45  
50  
55  
60  
65  
70  
75  
80  
85  
90  
95  
100  
105  
110  
115  
120  
125  
130  
135  
140  
145  
150  
155  
160  
165  
170  
175  
180  
185  
190  
195  
200  
205  
210  
215  
220  
225  
230  
235  
240  
245  
250  
255  
260  
265  
270  
275  
280  
285  
290  
295  
300  
305  
310  
315  
320  
325  
330  
335  
340  
345  
350  
355  
360  
365  
370  
375  
380  
385  
390  
395  
400  
405  
410  
415  
420  
425  
430  
435  
440  
445  
450  
455  
460  
465  
470  
475  
480  
485  
490  
495  
500  
505  
510  
515  
520  
525  
530  
535  
540  
545  
550  
555  
560  
565  
570  
575  
580  
585  
590  
595  
600  
605  
610  
615  
620  
625  
630  
635  
640  
645  
650  
655  
660  
665  
670  
675  
680  
685  
690  
695  
700  
705  
710  
715  
720  
725  
730  
735  
740  
745  
750  
755  
760  
765  
770  
775  
780  
785  
790  
795  
800  
805  
810  
815  
820  
825  
830  
835  
840  
845  
850  
855  
860  
865  
870  
875  
880  
885  
890  
895  
900  
905  
910  
915  
920  
925  
930  
935  
940  
945  
950  
955  
960  
965  
970  
975  
980  
985  
990  
995  
1000  
1005  
1010  
1015  
1020  
1025  
1030  
1035  
1040  
1045  
1050  
1055  
1060  
1065  
1070  
1075  
1080  
1085  
1090  
1095  
1100  
1105  
1110  
1115  
1120  
1125  
1130  
1135  
1140  
1145  
1150  
1155  
1160  
1165  
1170  
1175  
1180  
1185  
1190  
1195  
1200  
1205  
1210  
1215  
1220  
1225  
1230  
1235  
1240  
1245  
1250  
1255  
1260  
1265  
1270  
1275  
1280  
1285  
1290  
1295  
1300  
1305  
1310  
1315  
1320  
1325  
1330  
1335  
1340  
1345  
1350  
1355  
1360  
1365  
1370  
1375  
1380  
1385  
1390  
1395  
1400  
1405  
1410  
1415  
1420  
1425  
1430  
1435  
1440  
1445  
1450  
1455  
1460  
1465  
1470  
1475  
1480  
1485  
1490  
1495  
1500  
1505  
1510  
1515  
1520  
1525  
1530  
1535  
1540  
1545  
1550  
1555  
1560  
1565  
1570  
1575  
1580  
1585  
1590  
1595  
1600  
1605  
1610  
1615  
1620  
1625  
1630  
1635  
1640  
1645  
1650  
1655  
1660  
1665  
1670  
1675  
1680  
1685  
1690  
1695  
1700  
1705  
1710  
1715  
1720  
1725  
1730  
1735  
1740  
1745  
1750  
1755  
1760  
1765  
1770  
1775  
1780  
1785  
1790  
1795  
1800  
1805  
1810  
1815  
1820  
1825  
1830  
1835  
1840  
1845  
1850  
1855  
1860  
1865  
1870  
1875  
1880  
1885  
1890  
1895  
1900  
1905  
1910  
1915  
1920  
1925  
1930  
1935  
1940  
1945  
1950  
1955  
1960  
1965  
1970  
1975  
1980  
1985  
1990  
1995  
2000  
2005  
2010  
2015  
2020  
2025  
2030  
2035  
2040  
2045  
2050  
2055  
2060  
2065  
2070  
2075  
2080  
2085  
2090  
2095  
2100  
2105  
2110  
2115  
2120  
2125  
2130  
2135  
2140  
2145  
2150  
2155  
2160  
2165  
2170  
2175  
2180  
2185  
2190  
2195  
2200  
2205  
2210  
2215  
2220  
2225  
2230  
2235  
2240  
2245  
2250  
2255  
2260  
2265  
2270  
2275  
2280  
2285  
2290  
2295  
2300  
2305  
2310  
2315  
2320  
2325  
2330  
2335  
2340  
2345  
2350  
2355  
2360  
2365  
2370  
2375  
2380  
2385  
2390  
2395  
2400  
2405  
2410  
2415  
2420  
2425  
2430  
2435  
2440  
2445  
2450  
2455  
2460  
2465  
2470  
2475  
2480  
2485  
2490  
2495  
2500  
2505  
2510  
2515  
2520  
2525  
2530  
2535  
2540  
2545  
2550  
2555  
2560  
2565  
2570  
2575  
2580  
2585  
2590  
2595  
2600  
2605  
2610  
2615  
2620  
2625  
2630  
2635  
2640  
2645  
2650  
2655  
2660  
2665  
2670  
2675  
2680  
2685  
2690  
2695  
2700  
2705  
2710  
2715  
2720  
2725  
2730  
2735  
2740  
2745  
2750  
2755  
2760  
2765  
2770  
2775  
2780  
2785  
2790  
2795  
2800  
2805  
2810  
2815  
2820  
2825  
2830  
2835  
2840  
2845  
2850  
2855  
2860  
2865  
2870  
2875  
2880  
2885  
2890  
2895  
2900  
2905  
2910  
2915  
2920  
2925  
2930  
2935  
2940  
2945  
2950  
2955  
2960  
2965  
2970  
2975  
2980  
2985  
2990  
2995  
3000  
3005  
3010  
3015  
3020  
3025  
3030  
3035  
3040  
3045  
3050  
3055  
3060  
3065  
3070  
3075  
3080  
3085  
3090  
3095  
3100  
3105  
3110  
3115  
3120  
3125  
3130  
3135  
3140  
3145  
3150  
3155  
3160  
3165  
3170  
3175  
3180  
3185  
3190  
3195  
3200  
3205  
3210  
3215  
3220  
3225  
3230  
3235  
3240  
3245  
3250  
3255  
3260  
3265  
3270  
3275  
3280  
3285  
3290  
3295  
3300  
3305  
3310  
3315  
3320  
3325  
3330  
3335  
3340  
3345  
3350  
3355  
3360  
3365  
3370  
3375  
3380  
3385  
3390  
3395  
3400  
3405  
3410  
3415  
3420  
3425  
3430  
3435  
3440  
3445  
3450  
3455  
3460  
3465  
3470  
3475  
3480  
3485  
3490  
3495  
3500  
3505  
3510  
3515  
3520  
3525  
3530  
3535  
3540  
3545  
3550  
3555  
3560  
3565  
3570  
3575  
3580  
3585  
3590  
3595  
3600  
3605  
3610  
3615  
3620  
3625  
3630  
3635  
3640  
3645  
3650  
3655  
3660  
3665  
3670  
3675  
3680  
3685  
3690  
3695  
3700  
3705  
3710  
3715  
3720  
3725  
3730  
3735  
3740  
3745  
3750  
3755  
3760  
3765  
3770  
3775  
3780  
3785  
3790  
3795  
3800  
3805  
3810  
3815  
3820  
3825  
3830  
3835  
3840  
3845  
3850  
3855  
3860  
3865  
3870  
3875  
3880  
3885  
3890  
3895  
3900  
3905  
3910  
3915  
3920  
3925  
3930  
3935  
3940  
3945  
3950  
3955  
3960  
3965  
3970  
3975  
3980  
3985  
3990  
3995  
4000  
4005  
4010  
4015  
4020  
4025  
4030  
4035  
4040  
4045  
4050  
4055  
4060  
4065  
4070  
4075  
4080  
4085  
4090  
4095  
4100  
4105  
4110  
4115  
4120  
4125  
4130  
4135  
4140  
4145  
4150  
4155  
4160  
4165  
4170  
4175  
4180  
4185  
4190  
4195  
4200  
4205  
4210  
4215  
4220  
4225  
4230  
4235  
4240  
4245  
4250  
4255  
4260  
4265  
4270  
4275  
4280  
4285  
4290  
4295  
4300  
4305  
4310  
4315  
4320  
4325  
4330  
4335  
4340  
4345  
4350  
4355  
4360  
4365  
4370  
4375  
4380  
4385  
4390  
4395  
4400  
4405  
4410  
4415  
4420  
4425  
4430  
4435  
4440  
4445  
4450  
4455  
4460  
4465  
4470  
4475  
4480  
4485  
4490  
4495  
4500  
4505  
4510  
4515  
4520  
4525  
4530  
4535  
4540  
4545  
4550  
4555  
4560  
4565  
4570  
4575  
4580  
4585  
4590  
4595  
4600  
4605  
4610  
4615  
4620  
4625  
4630  
4635  
4640  
4645  
4650  
4655  
4660  
4665  
4670  
4675  
4680  
4685  
4690  
4695  
4700  
4705  
4710  
4715  
4720  
4725  
4730  
4735  
4740  
4745  
4750  
4755  
4760  
4765  
4770  
4775  
4780  
4785  
4790  
4795  
4800  
4805  
4810  
4815  
4820  
4825  
4830  
4835  
4840  
4845  
4850  
4855  
4860  
4865  
4870  
4875  
4880  
4885  
4890  
4895  
4900  
4905  
4910  
4915  
4920  
4925  
4930  
4935  
4940  
4945  
4950  
4955  
4960  
4965  
4970  
4975  
4980  
4985  
4990  
4995  
5000  
5005  
5010  
5015  
5020  
5025  
5030  
5035  
5040  
5045  
5050  
5055  
5060  
5065  
5070  
5075  
5080  
5085  
5090  
5095  
5100  
5105  
5110  
5115  
5120  
5125  
5130  
5135  
5140  
5145  
5150  
5155  
5160  
5165  
5170  
5175  
5180  
5185  
5190  
5195  
5200  
5205  
5210  
5215  
5220  
5225  
5230  
5235  
5240  
5245  
5250  
5255  
5260  
5265  
5270  
5275  
5280  
5285  
5290  
5295  
5300  
5305  
5310  
5315  
5320  
5325  
5330  
5335  
5340  
5345  
5350  
5355  
5360  
5365  
5370  
5375  
5380  
5385  
5390  
5395  
5400  
5405  
5410  
5415  
5420  
5425  
5430  
5435  
5440  
5445  
5450  
5455  
5460  
5465  
5470  
5475  
5480  
5485  
5490  
5495  
5500  
5505  
5510  
5515  
5520  
5525  
5530  
5535  
5540  
5545  
5550  
5555  
5560  
5565  
5570  
5575  
5580  
5585  
5590  
5595  
5600  
5605  
5610  
5615  
5620  
5625  
5630  
5635  
5640  
5645  
5650  
5655  
5660  
5665  
5670  
5675  
5680  
5685  
5690  
5695  
5700  
5705  
5710  
5715  
5720  
5725  
5730  
5735  
5740  
5745  
5750  
5755  
5760  
5765  
5770  
5775  
5780  
5785  
5790  
5795  
5800  
5805  
5810  
5815  
5820  
5825  
5830  
5835  
5840  
5845  
5850  
5855  
5860  
5865  
5870  
5875  
5880  
5885  
5890  
5895  
5900  
5905  
5910  
5915  
5920  
5925  
5930  
5935  
5940  
5945  
5950  
5955  
5960  
5965  
5970  
5975  
5980  
5985  
5990  
5995  
6000  
6005  
6010  
6015  
6020  
6025  
6030  
6035  
6040  
6045  
6050  
6055  
6060  
6065  
6070  
6075  
6080  
6085  
6090  
6095  
6100  
6105  
6110  
6115  
6120  
6125  
6130  
6135  
6140  
6145  
6150  
6155  
6160  
6165  
6170  
6175  
6180  
6185  
6190  
6195  
6200  
6205  
6210  
6215  
6220  
6225  
6230  
6235  
6240  
6245  
6250  
6255  
6260  
6265  
6270  
6275  
6280  
6285  
6290  
6295  
6300  
6305  
6310  
6315  
6320  
6325  
6330  
6335  
6340  
6345  
6350  
6355  
6360  
6365  
6370  
6375  
6380  
6385  
6390  
6395  
6400  
6405  
6410  
6415  
6420  
6425  
6430  
6435  
6440  
6445  
6450  
6455  
6460  
6465  
6470  
6475  
6480  
6485  
6490  
6495  
6500  
6505  
6510  
6515  
6520  
6525  
6530  
6535  
6540  
6545  
6550  
6555  
6560  
6565  
6570  
6575  
6580  
6585  
6590  
6595  
6600  
6605  
6610  
6615  
6620  
6625  
6630  
6635  
6640  
6645  
6650  
6655  
6660  
6665  
6670  
6675  
6680  
6685  
6690  
6695  
6700  
6705  
6710  
6715  
6720  
6725  
6730  
6735  
6740  
6745  
6750  
6755  
6760  
6765  
6770  
6775  
6780  
6785  
6790  
6795  
6800  
6805  
6810  
6815  
6820  
6825  
6830  
6835  
6840  
6845  
6850  
6855  
6860  
6865  
6870  
6875  
6880  
6885  
6890  
6895  
6900  
6905  
6910  
6915  
6920  
6925  
6930  
6935  
6940  
6945  
6950  
6955  
6960  
6965  
6970  
6975  
6980  
6985  
6990  
6995  
7000  
7005  
7010  
7015  
7020  
7025  
7030  
7035  
7040  
7045  
7050  
7055  
7060  
7065  
7070  
7075  
7080  
7085  
7090  
7095  
7100  
7105  
7110  
7115  
7120  
7125  
7130  
7135  
7140  
7145  
7150  
7155  
7160  
7165  
7170  
7175  
7180  
7185  
7190  
7195  
7200  
7205  
7210  
7215  
7220  
7225  
7230  
7235  
7240  
7245  
7250  
7255  
7260  
7265  
7270  
7275  
7280  
7285  
7290  
7295  
7300  
7305  
7310  
7315  
7320  
7325  
7330  
7335  
7340  
7345  
7350  
7355  
7360  
7365  
7370  
7375  
7380  
7385  
7390  
7395  
7400  
7405  
7410  
7415  
7420  
7425  
7430  
7435  
7440  
7445  
7450  
7455  
7460  
7465  
7470  
7475  
7480  
7485  
7490  
7495  
7500  
7505  
7510  
7515  
7520  
7525  
7530  
7535  
7540  
7545  
7550  
7555  
7560  
7565  
7570  
7575  
7580  
7585  
7590  
7595  
7600  
7605  
7610  
7615  
7620  
7625  
7630  
7635  
7640  
7645  
7650  
7655  
7660  
7665  
7670  
7675  
7680  
7685  
7690  
7695  
7700  
7705  
7710  
7715  
7720  
7725  
7730  
7735  
7740  
7745  
7750  
7755  
7760  
7765  
7770  
7775  
7780  
7785  
7790  
7795  
7800  
7805  
7810  
7815  
7820  
7825  
7830  
7835  
7840  
7845  
7850  
7855  
7860  
7865  
7870  
7875  
7880  
7885  
7890  
7895  
7900  
7905  
7910  
7915  
7920  
7925  
7930  
7935  
7940  
7945  
7950  
7955  
7960  
7965  
7970  
7975  
7980  
7985  
7990  
7995  
8000  
8005  
8010  
8015  
8020  
8025  
8030  
8035  
8040  
8045  
8050  
8055  
8060  
8065  
8070  
8075  
8080  
8085  
8090  
8095  
8100  
8105  
8110  
8115  
8120  
8125  
8130  
8135  
8140  
8145  
8150  
8155  
8160  
8165  
8170  
8175  
8180  
8185  
8190  
8195  
8200  
8205  
8210  
8215  
8220  
8225  
8230  
8235  
8240  
8245  
8250  
8255  
8260  
8265  
8270  
8275  
8280  
8285  
8290  
8295  
8300  
8305  
8310  
8315  
8320  
8325  
8330  
8335  
8340  
8345  
8350  
8355  
8360  
8365  
8370  
8375  
8380  
8385  
8390  
8395  
8400  
8405  
8410  
8415  
8420  
8425  
8430  
8435  
8440  
8445  
8450  
8455  
8460  
8465  
8470  
8475  
8480  
8485  
8490  
8495  
8500  
8505  
8510  
8515  
8520  
8525  
8530  
8535  
8540  
8545  
8550  
8555  
8560  
8565  
8570  
8575  
8580  
8585  
8590  
8595  
8600  
8605  
8610  
8615  
8620  
8625  
8630  
8635  
8640  
8645  
8650  
8655  
8660  
8665  
8670  
8675  
8680  
8685  
8690  
8695  
8700  
8705  
8710  
8715  
8720  
8725  
8730  
8735  
8740  
8745  
8750  
8755  
8760  
8765  
8770  
8775  
8780  
8785  
8790  
8795  
8800  
8805  
8810  
8815  
8820  
8825  
8830  
8835  
8840  
8845  
8850  
8855  
8860  
8865  
8870  
8875  
8880  
8885  
8890  
8895  
8900  
8905  
8910  
8915  
8920  
8925  
8930  
8935  
8940  
8945  
8950  
8955  
8960  
8965  
8970  
8975  
8980  
8985  
8990  
8995  
9000  
9005  
9010  
9015  
9020  
9025  
9030  
9035  
9040  
9045  
9050  
9055  
9060  
9065  
9070  
9075  
9080  
9085  
9090  
9095  
9100  
9105  
9110  
9115  
9120  
9125  
9130  
9135  
9140  
9145  
9150  
9155  
9160  
9165  
9170  
9175  
9180  
9185  
9190  
9195  
9200  
9205  
9210  
9215  
9220  
9225  
9230  
9235  
9240  
9245  
9250  
9255  
9260  
9265  
9270  
9275  
9280  
9285  
9290  
9295  
9300  
9305  
9310  
9315  
9320  
9325  
9330  
9335  
9340  
9345  
9350  
9355  
9360  
9365  
9370  
9375  
9380  
9385  
9390  
9395  
9400  
9405  
9410  
9415  
9420  
9425  
9430  
9435  
9440  
9445  
9450  
9455  
9460  
9465  
9470  
9475  
9480  
9485  
9490  
9495  
9500  
9505  
9510  
9515  
9520  
9525  
9530  
9535  
9540  
9545  
9550  
9555  
9560  
9565  
9570  
9575  
9580  
9585  
9590  
9595  
9600  
9605  
9610  
9615  
9620  
9625  
9630  
9635  
9640  
9645  
9650  
9655  
9660  
9665  
9670  
9675  
9680  
9685  
9690  
9695  
9700  
9705  
9710  
9715  
9720  
9725  
9730  
9735  
9740  
9745  
9750  
9755  
9760  
9765  
9770  
9775  
9780  
9785  
9790  
9795  
9800  
9805  
9810  
9815  
9820  
9825  
9830  
9835  
9840  
9845  
9850  
9855  
9860  
9865  
9870  
9875  
9880  
9885  
9890  
9895  
9900  
9905  
9910  
9915  
9920  
9925  
9930  
9935  
9940  
9945  
9950  
9955  
9960  
9965  
9970  
9975  
9980  
9985  
9990  
9995  
10000  
10005  
10010  
10015  
10020  
10025  
10030  
10035  
10040  
10045  
10050  
10055  
10060  
10065  
10070  
10075  
10080  
10085  
10090  
10095  
10100  
10105  
10110  
10115  
10120  
10125  
10130  
10135  
10140  
10145  
10150  
10155  
10160  
10165  
10170  
101

repulsion force under all separation distances, whereas tantalum has the lowest repulsive interaction barrier. Also, one can observe in Ta that the repulsive barrier due to desorption of the surfactant is broken (slope reversal) close to the surface. The barrier layer for copper lies in between the Ta and silica layers.

5           The high relative repulsive force between silica particles and the underlying silicon dioxide film indicates the formation of a soft shell structure on both the silica particles and the silicon dioxide film. The shell structure may be a single or a multiple layer, such as a micelle. The high repulsive force minimizes the CMP removal rate of silicon dioxide by isolating the silica particles from the silicon dioxide surface.

10           The surfactant adsorption on the copper film is measurable but weak as evidenced by the weak repulsive force shown in FIG. 10. This leads to some removal of copper during the tantalum polishing process, although the rate of polishing is reduced by the measurable surfactant adsorption on the copper surface.

15           The repulsive force shown is the lowest between the silica particles and the tantalum film. This is believed to be either due to little adsorption of selective adsorption additive on tantalum. Alternatively or additionally, the surfactant structure formed may have a low bond strength or elastic strength which may break up or disappears upon application of a load. Thus, since surfactant is not strongly or even generally measurably adsorbed by the tantalum layer, the abrasive silica particle can preferentially polish the tantalum layer.

Example 2 : Surfactant effect.

In this example, the removal rates of tantalum, copper and silicon dioxide films were investigated by varying the surfactant concentration of surfactants such as SAS, CTAB, TRITON X-100® and TWEEN-80®, and KETJENLUBE 522®. It is noted that alkali metal based surfactants can be replaced with non-alkali based ions if alkali contamination concerns are present. The CMC values for specific surfactants are given below.

The removal rates of the three films using different surfactants and the resulting Ta/Cu/silicon dioxide selectivity values are shown in Table 1. The concentration of each surfactant was set at 1 CMC. The bulk CMC values for various surfactants varies significantly and can depend on factors such as the nature of the hydrophilic head and hydrophobic tails groups, presence of counter ions and co-ions and temperature. The CMC values for C<sub>8</sub>TAB, C<sub>10</sub>TAB, C<sub>12</sub>TAB, and C<sub>16</sub>TAB, C<sub>14</sub>TAB and TRITON-X-100® are 144 mM, 66 mM, 15 mM, 0.9 mM, 0.23mM, and 3.6 mM, respectively.

Other slurry components were 20 mM BTA, 5 wt. % silica particles having sizes around 0.5 µm. The slurry had a pH of 9. The pad pressure was 6.7 psi, while the linear velocity was 253 ft/min. The table below shows that the removal rates of silicon dioxide is decreased as the carbon chain length of CTAB is lengthened from 8 to 14. The chain length changes the length of the hydrophobic part of the surfactant and thus strengthens the micelle interaction.

Table 1. The removal rates of tantalum/copper/silicon dioxide using different surfactants

		Surfactant					
		No additive	C <sub>8</sub> TAB	C <sub>12</sub> TAB	C <sub>10</sub> TAB	C <sub>14</sub> TAB	TRITON X-100®
Removal Rate (nm/min)	Ta	335.1	147.5	34.4	450	208.8	227.0
	Cu	31.8	27.7	19.6	32.6	40.9	16.6
	Silicon dioxide	392.1	0.1	0.2	0.1	0.1	341.2
Selectivity of Ta/SiO <sub>2</sub>		0.85	1475	172	450	2088	0.67
Selectivity of Cu/SiO <sub>2</sub>		0.08	277	98	326	409	0.05
Selectivity of Ta/Cu		10.5	5.32	1.75	1.38	5.105	13.67

The above table shows that TRITON X-100® does not substantially increase the metal to dielectric selectivity. Thus, only specific surfactants in specific concentrations are generally helpful. The SAR values for CTAB having 8 to 14 carbons can be as high as 2500, strongly showing the selective adsorption effect.

### Example 3: Surfactant concentration effect.

As shown in Example 2, C<sub>12</sub>TAB can produce selective adsorption on certain materials. In this example, the effect of varying the C<sub>12</sub>TAB concentration was investigated. The concentration of C<sub>12</sub>TAB was varied from 0 to 64 mM. The slurry included 5 wt.% silica particles having sizes of approximately 0.3 μm and 20 mM BTA. The pH was held at a constant value of 9. The pressure on the sample was 6.7 psi, while the linear velocity was 253 ft/min.

The resulting polish rates and selectivity of tantalum/copper/silicon dioxide are shown in Table 2 below. Table 2 demonstrates that the removal rates and selectivity of materials can be controlled by varying the surfactant concentration, the surfactant here being C<sub>12</sub>TAB. At very



low surfactant concentrations, the Ta/SiO<sub>2</sub> selectivity is low, such as <1. The selectivity of Ta/SiO<sub>2</sub> can be increased to 1500 or more when the surfactant concentration is optimized at a higher level as described below. The SAR<sub>Ta/Cu</sub> can also be greater than 5 using the C<sub>12</sub>TAB surfactant, while still providing a minimal silicon dioxide removal rate. Thus, by controlling the surfactant and its concentration, the AR, SAR and selectivity values can be accordingly modified.

When 1 mM of C<sub>12</sub>TAB was added to the slurry, the SiO<sub>2</sub> polishing rate was still very high, being approximately 350 nm/minute, the Ta removal rate was 330 nm/min, while the Cu polishing rate was 26 nm/min. Under these conditions, the selectivity of Ta/SiO<sub>2</sub> was 0.89, the selectivity of Cu/SiO<sub>2</sub> was 0.07 and the selectivity of Ta/Cu was 12.70.

The data indicates that above a certain concentration of surfactant between (1 mM and 4 mM), the AR values of the dielectric, SAR values of Ta to SiO<sub>2</sub>, and tantalum to SiO<sub>2</sub> selectivity increase by more than 3 orders of magnitude, from less than 1.0 to over 1000. This surfactant interaction can be defined as a Type I interaction. A Type I interaction shows substantial non-linear increase in AR values of the dielectric above a specific surfactant additive concentration, whereas for a Type II interaction, the adsorption increase is more linear in nature. Typically, a silicon dioxide surface shows a Type I interaction behavior whereas metals/refractory barriers show Type II adsorption behavior. After a rapid increase in the selectivity, with a further increase in surfactant concentration the selectivity starts to decrease due to a reduced polish rate of the metal. It should be noted that the planarity and surface defectivity such as dishing, erosion and dielectric loss, can also be controlled by appropriate selection of surfactant concentration provided to the slurry.

Table 2. Surfactant concentration effect

		Concentration of C <sub>12</sub> TAB			
		No C <sub>12</sub> TAB	4 mM	16 mM	64 mM
Removal Rate (nm/min)	Ta	335.1	335.3	174.9	9.2
	Cu	31.8	4.4	9.0	9.0
	Silicon dioxide	392.1	0.20	0.2	0.1
Selectivity of Ta/SiO <sub>2</sub>		0.85	1676.5	875	92
Selectivity of Cu/SiO <sub>2</sub>		0.08	22	45	90
Selectivity of Ta/Cu		10.53	16.2	19.4	1.0

#### Example 4: Particle size effect

In this Example, silica particles in the slurry were provided in sizes ranging from 0.05  $\mu\text{m}$  to 1  $\mu\text{m}$ . The concentration of silica particles was 5% by weight. The slurry included 20 mM BTA and 16 mM C<sub>12</sub>TAB. The pH was held at 9. The pad pressure was 6.7 psi and the linear velocity was 253 ft/min. Table 3 shows that the polishing rate of tantalum increased and then decreased quite substantially as the size of particles in the tantalum CMP slurry was increased, while holding the concentration of silica particles constant in the slurry.

The removal rates of copper and silicon dioxide did not significantly change as the particle size was varied. This is likely due to a chemically modified layer and surfactant layer, respectively. However, the surface defectivity of copper was found to increase with the increasing particle size. These results suggest that there is the optimal particle size to achieve a higher removal rate of tantalum and a high tantalum/copper/silicon dioxide selectivity.

Table 3. Effect of the particle size on tantalum CMP

		Particle size ( $\mu\text{m}$ )			
		0.2	0.3	0.5	1.0
Removal Rate (nm/min)	Ta	20.8	174.9	34.4	13.0
	Cu	28.2	9.0	19.6	12.0
	Silicon dioxide	0.2	0.2	0.2	0.2
Selectivity of Ta/SiO <sub>2</sub>		104	875	172	65
Selectivity of Cu/SiO <sub>2</sub>		14	45	98	48
Selectivity of Ta/Cu		0.74	19.5	1.76	1.2

Example 5: Particle concentration effect.

In this example, the effect of particle concentration on tantalum CMP was considered. The slurry included 20 mM BTA and 16 mM C<sub>12</sub>TAB, held at a pH of 9. The pad pressure was 6.7 psi and the linear velocity was 253 ft/min. Table 4 shows a higher removal rate of tantalum for increasing particle concentration. The selectivity to tantalum/copper/silicon dioxide was not changed significantly with varying particle concentration.

Table 4. Particle concentration effect on the tantalum CMP

		Particle concentration	
		5 wt.%	10 wt.%
Removal Rate (nm/min)	Ta	174.9	229.1
	Cu	9.0	11.9
	Silicon dioxide	0.2	0.40
Selectivity of Ta/SiO <sub>2</sub>		875	573
Selectivity of Cu/SiO <sub>2</sub>		45	30.0
Selectivity of Ta/Cu		19.4	19.3

### Example 6: Effect of pH

Table 5 shows the effect on CMP for different pH values. The slurry used included 20 mM BTA, 16 mM C<sub>12</sub>TAB and 5 wt. % silica particles having sizes of approximately 0.5 µm. The pressure on the samples was 6.7 psi, while the linear velocity was 253 ft/min. The pH was varied from 1 to 13. Table 5 shows that removal rates were increased as the pH was increased, and that the change in removal rates at different pHs were dependent upon the materials. The increased polishing rate for tantalum with increasing pH (up to a pH of 9) may result from chemical interactions with the silica particles.

Table 5. Effect of pH on the removal rates

		PH			
		4	7	9	11
Removal Rate (nm/min)	Ta	8.4	9.6	34.4	23.3
	Cu	36.2	37.2	19.6	41.7
	Silicon dioxide			0.2 0.0	
Selectivity of Ta/SiO <sub>2</sub>		0.62	1.17	172	116.5
Selectivity of Cu/SiO <sub>2</sub>		2.70	4.53	98	208.5
Selectivity of Ta/Cu		0.23	0.260	1.76	0.560

### Example 7: CMP polishing rate as a function of polishing pressure

This Example shows the removal rate of tantalum/tantalum nitride, copper and silicon dioxide polishing as a function of polishing pressure. In this Example, the polishing pressure was varied from 0.5 psi to 10 psi. The CMP slurry included 20 mM BTA, 16 mM C<sub>12</sub>TAB and 5

wt.% silica particles having sizes of approximately 0.5  $\mu\text{m}$ . The pH of slurry was held constant at 9.

Table 6 shows that the removal rate of tantalum increases with pressure, whereas the removal rates of copper and silicon dioxide are essentially invariant to changes in polishing pressure. The pressure invariance of copper and silicon dioxide films may result from formation of a Cu-BTA layer and the selective adsorption of  $\text{C}_{12}\text{TAB}$  on silicon dioxide and abrasive particle surfaces. From these results, it can be concluded that the removal rate of tantalum/tantalum nitride and the selectivity of Ta/Cu/silicon dioxide can be optimized using polishing pressure.

Table 6. CMP polish rate as a function of pressure

		Pad Pressure (psi)			
		2.7	4.3	6.7	8.7
Removal Rate (nm/min)	Ta	4.6	6.3	34.4	40.1
	Cu	8.2	10.1	19.6	38.9
	Silicon dioxide	0.2	0.2	0.2	0.2
Selectivity of Ta/ $\text{SiO}_2$		23	31.5	172	200.5
Selectivity of Cu/ $\text{SiO}_2$		41	50.5	98	195.0
Selectivity of Ta/Cu		0.57	0.623	1.75	1.03

#### Example 8: Hydrogen peroxide concentration effect

This Example shows the effect of varying the concentration of an oxidant on CMP removal rates for tantalum, copper and silicon dioxide. The concentration of hydrogen peroxide in a slurry containing 20 mM BTA, 16 mM  $\text{C}_{12}\text{TAB}$  and 5 wt. % silica particles having sizes of

approximately 0.5  $\mu\text{m}$  was varied from 0 to 10 wt. %. The experiments were conducted at 6.7 psi. The pH during polishing was maintained at 9.0. The linear velocity during the polishing process was approximately 253 ft/min.

Table 7 shows the results of tantalum CMP for different hydrogen peroxide concentrations. As shown, the Cu polishing rate is more sensitive to the hydrogen peroxide concentration, as compared to both  $\text{SiO}_2$  and Ta. A 2% hydrogen peroxide concentration was found to provide high selectivity for both Ta/ $\text{SiO}_2$  and Ta/Cu.

Table 7. The performance of the tantalum CMP as a function of the concentration of hydrogen peroxide.

		Concentration of $\text{H}_2\text{O}_2$		
		No $\text{H}_2\text{O}_2$	2 wt. %	5 wt. %
Removal Rate (nm/min)	Ta	34.4	37.1	32.9
	Cu	19.6	2.0	5.4
	Silicon dioxide	0.2	0.2	0.1
Selectivity of Ta/ $\text{SiO}_2$		172	186	165.0
Selectivity of Cu/ $\text{SiO}_2$		98	10	56.0
Selectivity of Ta/Cu		1.76	18.6	6.1

#### Example 9: Effect of a weak complexing agent

In this Example, citric acid was added to a slurry to enhance the CMP removal rates of tantalum. Table 8 shows the CMP polish rates of tantalum/copper/silicon dioxide layers with a slurry including 20 mM of BTA, 16 mM  $\text{C}_{12}\text{TAB}$  and 5 wt. % silica particles having sizes of

approximately 0.5  $\mu\text{m}$ . The concentration of citric acid was varied from 0 to 50 mM. The slurry pH was kept at 9. The pressure was 6.7 psi and the linear velocity was 253 ft/min.

The results show that the CMP polish rate of tantalum increased when the concentration of citric acid was increased. The data also shows that the removal rates of copper and silicon dioxide were not substantially changed even when high concentrations of citric acid (e.g. 50 mM) were added to the slurry.

Table 8. The effect of citric acid on the Ta CMP

		Concentration of citric acid		
		No citric acid	10 mM	50 mM
Removal Rate (nm/min)	Ta	34.4	41	127.2
	Cu	19.6	12.9	18.9
	Silicon dioxide	0.2	0.5	0.1
Selectivity of Ta/SiO <sub>2</sub>		172	205.0	1272
Selectivity of Cu/SiO <sub>2</sub>		98	65.0	189
Selectivity of Ta/Cu		1.76	3.20	6.73

#### Example 10 : BTA effect

In this Example, the removal rates of tantalum, copper and silicon dioxide films were investigated by varying the concentration of BTA in the slurry. The slurry included 16 mM C<sub>12</sub>TAB and 5 wt. % silica particles having an average size of around 0.5  $\mu\text{m}$ , the solution having a pH of 9. The concentration of BTA was varied from 0 to 50 mM. The pressure on the samples was 6.7 psi, while the linear velocity used was 253 ft/min.

Table 9 shows the effect of BTA on the polishing rate of tantalum, copper and silicon dioxide. The polishing rate of copper is seen to decrease gradually as the concentration of BTA is increased due to inhibiting copper oxide formation during CMP. On the other hand, the removal rate of tantalum and silicon dioxide are not apparently influenced by the addition of BTA to the slurry. In addition, less copper surface defects were observed when BTA was added to the slurry.

Table 9. Effect of BTA on the performance of the tantalum CMP slurry

		Concentration of BTA			
		No inhibitor	BTA		
		BTA	1 mM	5 mM	20 mM
Removal Rate (nm/min)	Ta	65.5	31.2	8.4	34.4
	Cu	46.6	53.8	23.5	19.6
	Silicon dioxide	1.8	4.0	3.6	0.2
Selectivity of Ta/SiO <sub>2</sub>		36.4	75	7.9	122
Selectivity of Cu/SiO <sub>2</sub>		25.9	12.8	6.5	98
Selectivity of Ta/Cu		1.4	0.58	1.21	1.76

Example 11: Dishing and erosion reduction from high Ta/Cu selectivity.

Good planarity can reduce the surface defectivity, such as dishing and erosion. One way to maintain good planarity is by limiting the thickness of tantalum oxide to less than 200 nm. In this Example, chemicals were added to the slurry to inhibit tantalum oxidation.

Both dishing and erosion defects are generally present on the incoming wafers for tantalum CMP because the slurry used for copper polishing generally has a higher polishing rate



for copper as compared to tantalum. To reduce the dishing and erosion, the tantalum CMP slurry preferably has a higher tantalum polishing rate compared to copper.

Experiments were conducted with a 2 step polish on patterned wafers to determine the resulting dishing and erosion characteristics. In the first CMP step, copper was polished using an iodine based slurry including .01 N iodine, 20 mM BTA and 5 mM citric acid at a pH of 4. Dishing was measured to be between 50 and 150 nm for a 50 micron line and 50% density and erosion of less than 5 nm for a 2 micron line was observed after the copper polishing process.

After the copper polishing process, the tantalum/copper layer was polished using a slurry containing 20 mM BTA, and 15 mM  $C_{12}TAB$ , 0.01 to 0.1 M citric acid at a pH of 9.0. BTA can act as a corrosion inhibitor for both copper and the tantalum layers. The dishing and corrosion values were measured. The dishing was found to be 80 nm, while the erosion was less than 5 nm. No visible dielectric loss was observed in the process. Thus, the tantalum polishing process can reduce dishing and provide negligible erosion and dielectric loss.

#### Example 12: Use of Low K dielectrics

The effect of surfactants and additives on AR, SAR and Selectivity values have been found to be similar if low dielectric constant materials, such as low K dielectric materials are used instead of  $SiO_2$ . This Examples shows that the adsorption ratio (AR), selective adsorption ratio (SAR), and selectivity of a low K silicon oxy-carbide material to surfactants and additives is similar to corresponding values for  $SiO_2$ . The oxy-carbide material has a dielectric constant of approximately 3.0. A slurry including 5 wt. % 0.3  $\mu m$  silica particles and 20 mM BTA

(PH of 9) used to polish the Ta and low K dielectric layers. 20 mM BTA represented approximately 1 CMC. The polish rate of the low K dielectric exceeded 500 nm/minute when no surfactant was used. However, the polishing rate dropped to less than 0.5 nm when 1 CMC C<sub>12</sub>TAB was used. Thus, a change in metal to dielectric selectivity achieved was approximately 1000 with the addition of 1 CMC of the surfactant C<sub>12</sub>TAB.

#### Example 13: Polishing of a TiN barrier metal

In this Example, TiN polishing was demonstrated. The slurry included 16 mM C<sub>12</sub>TAB, 20 mM BTA, and 0.1 M citric acid. 5 wt. % silica particles were provided having an average size of around 0.5  $\mu$ m. The slurry had a pH of 9. The pressure on the samples was 6.7 psi, while the linear velocity was 253 ft/min. A polishing rate of approximately 40 nm/min was measured for the TiN film.

#### Example 14: Single step CMP polish a structure including a gate or interconnect metal, refractory metal based film and a dielectric film

Slurries was prepared with 3 % by weight multiphase core particles formed from alumina particles (obtained from Nanophase Technologies Corporation, Romeoville, IL) which were coated with thin layers (< 50 nm) of silica using the Stober process. In the slurry formulation, 20 mM C<sub>12</sub>TAB, 20 mM BTA, 50 mM citric acid and 5% Hydrogen peroxide solutions were added. The pH was adjusted to 9.0. Polishing studies were conducted at 6.7 psi at 253 ft/min.

Under the above conditions, the polish rate for copper was 250 nm/per minute, the polish rate for tantalum was 150 nm per/minute and the polish rate for SiO<sub>2</sub> was < 0.5 nm/minute.

Thus, a selectivity of greater than 500 was obtained for Cu/SiO<sub>2</sub>, a selectivity of greater than 300 was obtained for Ta/SiO<sub>2</sub> and a selectivity of approximately 1.7 for Cu/Ta. Thus, the invention can be used for polishing a structure having a gate or interconnect metal, such as copper or silver and a refractory metal based layer, such as Ta, in a single step.

5           The single step slurry can be used to polish a Cu/refractory metal/dielectric structure and provide a Cu/refractory metal selectivity of at least 1, and a Cu/dielectric selectivity of at least 50. More preferably, the Cu/dielectric selectivity is at least 100, and most preferably at least 500. The single step slurry and method can also provide a refractory metal/dielectric selectivity of at least 50, more preferably at least 100, 250 or more, or most preferably at least 500.

It should be noted that good selectivity results can also be expected for multiphase silica coated quartz, silicon nitride or silicon carbide core particles, or other inner cores which are preferably harder than the SiO<sub>2</sub> or other dielectric provided by the structure for polishing. Given the high polish rates for copper, low polishing rate for the dielectric and an intermediate polishing rate for the refractory based metal layer (tantalum) demonstrated above, this slurry embodiment is particularly well suited for the single step slurry and method where a structure including a gate or interconnect metal and refractory metal based film can be polished in a single continuous polishing step with a single slurry composition. However, the above slurry can also be used to polish single layers, such as a refractory metal based barrier layer.

20           While the preferred embodiments of the invention have been illustrated and described, it will be clear that the invention is not so limited. Numerous modifications, changes, variations, substitutions and equivalents will occur to those skilled in the art without departing from the spirit and scope of the present invention as described in the claims.